

TECHNICAL DATA SHEET

TECHNYL A 216 V30 GY 90N

TECHNYL A 216 V30 GY 90N is a polyamide 66, reinforced with 30% of glass fiber, for injection moulding. This grade offers an excellent combination between thermal and mechanical properties.

General

Certifications	RoHS EC 1907/2006 (REACH)	UL listed product
Polymer type	PA66	
Applications	automotive applications handles	connectors white goods / small appliances
Colors available	black grey red	natural white
Forms	pellets	
Processing technology	injection moulding	

Product identification

ISO 1043 abbreviation	PA66-GF30
ISO 16396 designation	PA66,GF30,M,S14-100

Condition	Standard	Unit	Value
-----------	----------	------	-------

Physical properties

Density		ISO 1183	g/cm ³	1.37
Water absorption	24 hr, 23°C	ISO 62	%	0.8
Water absorption, saturation			%	5.3

TECHNICAL DATA SHEET

TECHNYL A 216 V30 GY 90N

	Condition	Standard	Unit	Value
Mechanical properties				dam / cond.*
Tensile modulus	1 mm/min	ISO 527-1/-2	MPa	10000 / 7100
Stress at break		ISO 527-1/-2	MPa	150 / 100
Strain at break		ISO 527-1/-2	%	2.6 / 5.6
Flexural modulus, ISO 178	2 mm/min	ISO 178	MPa	8400 / 5900
Flexural strength, ISO 178	2 mm/min	ISO 178	MPa	225 / 160
Charpy impact strength, +23°C	+23°C	ISO 179/1eU	kJ/m ²	45 / 55
Charpy notched impact strength, +23°C	+23°C	ISO 179/1eA	kJ/m ²	5.5 / 6.9

*: **conditioned according to ISO 1110**

	Condition	Standard	Unit	Value
Thermal properties				
Melting temperature, 10°C/min		ISO 11357-1	°C	262
Temp. of deflection under load, 0.45 MPa	0.45 MPa	ISO 75	°C	260
Temp. of deflection under load, 1.80 MPa	1.80 MPa	ISO 75	°C	255

	Condition	Standard	Unit	Value
Burning behaviour				
UL Yellow Card availability 1	<u>Click here to have access to the UL Yellow Card availability 1 -> QMF22.E44716</u>			
Flammability, 0.75 mm	0.75 mm	UL 94		HB
Flammability, 1.5 mm	1.5 mm	UL 94		HB
Flammability, 3.0 mm	3.0 mm	UL 94		HB
Oxygen index			%	23.0
Burning rate, FMVSS, Thickness 1 mm		FMVSS 302		<100 mm/min

Condition	Standard	Unit	Value
-----------	----------	------	-------

Electrical properties

Volume resistivity		IEC 62631-3-1	ohm.m	1.0E13
Surface resistivity		IEC 62631-3-1	ohm	6.1E16
Dielectric strength	1 mm	IEC 60243-1	kV/mm	22.0

Processing conditions

Drying temperature/time	80
Suggested max moisture	0.2 %
Rear temperature	270 - 280 °C
Middle temperature	275 - 285 °C
Front temperature	280 - 290 °C
Recommended mould temperature	70 - 100 °C

Injection notes

The material is supplied in airtight bags, ready for use. In case that the virgin material has absorbed moisture, it must be dried with a dehumidified air drying equipment, dew point minimum -20°C. Recommended time 2-4h.

Injection advice

For reinforced polyamides, Domo recommends the use of steel with a high content of carbon, and purified for polishing, to avoid or limit the abrasion. For example: X38CrMoV5-1 (EN Norm) - 1.2367 / 1.2343 (DIN Norm) or X160CrMoV12 (EN Norm) - 1.2601 / 1.2379 (DIN Norm). In the case of high requirements on surface quality a mould temperature of up to 120°C can be considered. The processing parameters like processing temperatures are a recommendation and can be adjusted in function of injection machine size, part geometry / design.