

TECHNICAL DATA SHEET

## TECHNYL A 218 NC

TECHNYL A 218 NC is an unreinforced polyamide 66, standard viscosity, heat stabilized for injection moulding. This grade offers all the primary properties of unreinforced polyamide 66. In addition, it has improved resistance to high temperature, and can be used for components which will withstand long-term temperature stresses

### General

Polymer type	PA66		
Certifications	RoHS EC 1907/2006 (REACH)	UL listed product	
Feature	heat-aging stabilized		
Applications	automotive applications electrical/electronic applications	connectors	fasteners
Colors available	black	natural	
Forms	pellets		
Processing technology	injection moulding		

### Product identification

ISO 1043 abbreviation	PA66
ISO 16396 designation	PA66,MH,S14-040

Condition	Standard	Unit	Value
-----------	----------	------	-------

### Physical properties

	Condition	Standard	Unit	Value
Density		ISO 1183	g/cm <sup>3</sup>	1.14
Humidity absorption	T=23°C, 50% RH	ISO 62	%	3.1 - 3.2
Water absorption	24 hr, 23°C	ISO 62	%	1.2 - 1.3
Water absorption, saturation			%	8.3
Molding shrinkage, parallel		ISO 294-4, 2577	%	1.6
Molding shrinkage, normal		ISO 294-4, 2577	%	1.6

	Condition	Standard	Unit	Value
<b>Mechanical properties</b>				<b>dam / cond.*</b>
Tensile modulus	1 mm/min	ISO 527-1/-2	MPa	3100 / 1300
Stress at break		ISO 527-1/-2	MPa	55 / 65
Strain at break		ISO 527-1/-2	%	30 / 300
Yield stress		ISO 527-1/-2	MPa	85 / 50
Flexural modulus, ISO 178	2 mm/min	ISO 178	MPa	3000 / 1300
Flexural modulus, ASTM D790	2 mm/min	ASTM D790	MPa	3300 / -
Flexural strength, ISO 178	2 mm/min	ISO 178	MPa	120 / 70
Flexural strength, ASTM D790	2 mm/min	ASTM D790	MPa	125 / -
Charpy notched impact strength, +23°C	+23°C	ISO 179/1eA	kJ/m <sup>2</sup>	5 / 15
Izod notched impact strength, +23°C	+23°C	ISO 180/1A	kJ/m <sup>2</sup>	4.5 / 10

\*: **conditioned according to ISO 1110**

	Condition	Standard	Unit	Value
<b>Thermal properties</b>				
Melting temperature, 10°C/min		ISO 11357-1	°C	262
Temp. of deflection under load, 1.80 MPa	1.80 MPa	ISO 75	°C	82

	Condition	Standard	Unit	Value
<b>Burning behaviour</b>				
UL Yellow Card availability 1	<b><u><a href="#">Click here to have access to the UL Yellow Card availability 1 -&gt; File Number: E44716</a></u></b>			
Flammability, 0.75 mm	0.75 mm	UL 94		V2
Flammability, 1.5 mm	1.5 mm	UL 94		V2
Flammability, 3.0 mm	3.0 mm	UL 94		V2
Glow-wire flammability index, GWFI, 1.5 mm	1.5 mm	IEC 60695-2-12	°C	650
Burning rate, FMVSS, Thickness 1 mm		FMVSS 302		<100 mm/min

Condition	Standard	Unit	Value
-----------	----------	------	-------

### Electrical properties


Condition	Standard	Unit	Value
Volume resistivity	IEC 62631-3-1	ohm.m	1.0E13
Surface resistivity	IEC 62631-3-1	ohm	1.0E15
Comparative tracking index	Solution A	IEC 60112	V
CTI performance level category	Sol A		PLC 1
Dielectric strength	1 mm	IEC 60243-1	kV/mm
			18.0

### Processing conditions

Drying temperature/time	80 °C
Suggested max moisture	0.2 %
Rear temperature	270 - 280 °C
Middle temperature	275 - 285 °C
Front temperature	280 - 290 °C
Recommended mould temperature	70 - 100 °C


**Stress-strain, dry**

Temperature (°C)



**Stress-strain, conditioned**

Temperature (°C)



### Injection notes

The material is supplied in airtight bags, ready for use. In case that the virgin material has absorbed moisture, it must be dried with a dehumidified air drying equipment, dew point minimum -20°C. Recommended time 2-4h.

### Injection advice

For unfilled polyamides, Domo recommends the use of high alloy steel with a low chromium content. For example: X38CrMoV5-1 (EN Norm) - 1.2367 / 1.2343 (DIN Norm). In the case of high requirements on surface quality a mould temperature of up to 120°C can be considered. The processing parameters like processing temperatures are a recommendation and can be adjusted in function of injection machine size, part geometry / design.