

TECHNICAL DATA SHEET

## TECHNYL A 218 V50 BK 21NK

TECHNYL A 218 V50 BK 21NK is a polyamide 66, reinforced with 50% of glass fibre, heat stabilized, for injection molding. This grade offers an excellent combination between thermal and mechanical properties.

### General

Certifications	RoHS	EC 1907/2006 (REACH)
Polymer type	PA66	
Feature	heat-aging stabilized high stiffness	high dimensional stability
Applications	automotive applications electrical/electronic applications	consumer applications
Colors available	black	
Forms	pellets	
Processing technology	injection moulding	

### Product identification

ISO 1043 abbreviation	PA66-GF50
ISO 16396 designation	PA66,GF50,MH,S14-160

Condition	Standard	Unit	Value
-----------	----------	------	-------

## Physical properties

Condition	Standard	Unit	Value
Density	ISO 1183	g/cm <sup>3</sup>	1.55
Humidity absorption	T=23°C, 50% RH (equivalent ISO 1110)	%	1.6 - 1.7
Water absorption	24 hr, 23°C, immersion in water, thickness 2mm	%	0.6
Water absorption, saturation		%	3.6
Molding shrinkage, parallel	ISO 294-4, 2577	%	0.3 - 0.5
Molding shrinkage, normal	ISO 294-4, 2577	%	0.6 - 0.8

Condition	Standard	Unit	Value
-----------	----------	------	-------

## Mechanical properties

dam / cond.\*

Condition	Standard	Unit	Value	
Tensile modulus	1 mm/min	ISO 527-1/-2	MPa	16200 / 12500
Stress at break		ISO 527-1/-2	MPa	240 / 175
Strain at break		ISO 527-1/-2	%	2.7 / 4
Flexural modulus, ISO 178	2 mm/min	ISO 178	MPa	14500 / 10000
Charpy impact strength, +23°C	+23°C	ISO 179/1eU	kJ/m <sup>2</sup>	95 / 95
Charpy notched impact strength, +23°C	+23°C	ISO 179/1eA	kJ/m <sup>2</sup>	14 / 18
Izod notched impact strength, +23°C	+23°C	ISO 180/1A	kJ/m <sup>2</sup>	15 / 17

\*: conditioned according to ISO 1110

Condition	Standard	Unit	Value
-----------	----------	------	-------

## Thermal properties

Condition	Standard	Unit	Value	
Melting temperature, 10°C/min		ISO 11357-1	°C	262
Temp. of deflection under load, 0.45 MPa	0.45 MPa	ISO 75	°C	260
Temp. of deflection under load, 1.80 MPa	1.80 MPa	ISO 75	°C	255

Condition	Standard	Unit	Value
-----------	----------	------	-------

## Burning behaviour

Glow-wire flammability index, GWFI, 0.75 mm	0.75 mm	IEC 60695-2-12	°C	650
Glow-wire flammability index, GWFI, 1.5 mm	1.5 mm	IEC 60695-2-12	°C	650
Glow-wire flammability index, GWFI, 3.0 mm			°C	650
Oxygen index			%	23.0
Burning rate, FMVSS, Thickness 1 mm		FMVSS 302		<100 mm/min

Condition	Standard	Unit	Value
-----------	----------	------	-------

## Electrical properties


Volume resistivity		IEC 62631-3-1	ohm.m	1.0E13
Surface resistivity		IEC 62631-3-1	ohm	6.0E12
Comparative tracking index	Solution A	IEC 60112	V	400.0
CTI performance level category		Sol A		PLC 1
Dielectric strength	1 mm	IEC 60243-1	kV/mm	35.0

## Processing conditions

Drying temperature/time	80
Suggested max moisture	0.2 %
Rear temperature	270 - 280 °C
Middle temperature	280 - 290 °C
Front temperature	280 - 300 °C
Recommended mould temperature	70 - 100 °C


### Stress-strain, dry

Temperature (°C)



### Stress-strain, conditioned

Temperature (°C)



### Injection notes

The material is supplied in airtight bags, ready for use. In case that the virgin material has absorbed moisture, it must be dried with a dehumidified air drying equipment, dew point minimum -20°C. Recommended time 2-4h.

### Injection advice

For reinforced polyamides, Domo recommends the use of steel with a high content of carbon, and purified for polishing, to avoid or limit the abrasion. For example: X38CrMoV5-1 (EN Norm) - 1.2367 /1.2343 (DIN Norm) or X160CrMoV12 (EN Norm) - 1.2601 /1.2379 (DIN Norm). In the case of high requirements on surface quality a mould temperature of up to 120°C can be considered. The processing parameters like processing temperatures are a recommendation and can be adjusted in function of injection machine size, part geometry / design.