

TECHNICAL DATA SHEET

TECHNYL A 239HR V30 NC

DOMAMID 66G30I1HR1H1 NC

Polyamide 66, 30% glass fiber reinforced, hydrolisis stabilized, impact modified, heat-aging stabilized, for injection moulding

General

Polymer type	PA66	
Certifications	RoHS	
Feature	heat-aging stabilized impact modified	hydrolysis stabilized
Processing technology	injection moulding	

Product identification

ISO 1043 abbreviation	PA66-I-GF30
ISO 16396 designation	PA66,GF30,MWHP,S14-090

Condition	Standard	Unit	Value
-----------	----------	------	-------

Physical properties

Density		ISO 1183	g/cm ³	1.35
Humidity absorption	T=23°C, 50% RH	ISO 62	%	2.2 - 2.4
Water absorption	24 hr, 23°C	ISO 62	%	0.8
Water absorption, saturation			%	5.3
Molding shrinkage, parallel		ISO 294-4, 2577	%	0.3 - 0.5
Molding shrinkage, normal		ISO 294-4, 2577	%	0.8 - 1.0
Melt volume-flow rate, MVR, 5.0 kg	275°C, 5kg	ISO 1133	cm ³ /10 min	45.0
Viscosity number	96% H2SO4	ISO 307	cm ³ /g	145.0

	Condition	Standard	Unit	Value
Mechanical properties				dam / cond.*
Tensile modulus	1 mm/min	ISO 527-1/-2	MPa	9000 / -
Stress at break	5 mm/min	ISO 527-1/-2	MPa	145 / -
Strain at break	5 mm/min	ISO 527-1/-2	%	2.5 / -
Flexural modulus, ISO 178	2 mm/min	ISO 178	MPa	8300 / -
Flexural strength, ISO 178	2 mm/min	ISO 178	MPa	210 / -
Charpy impact strength, +23°C	+23°C	ISO 179/1eU	kJ/m ²	65 / -
Charpy notched impact strength, +23°C	+23°C	ISO 179/1eA	kJ/m ²	15 / -
Izod impact strength, +23°C	+23°C	ISO 180/1U	kJ/m ²	60 / -
Izod notched impact strength, +23°C	+23°C	ISO 180/1A	kJ/m ²	15 / -

*: conditioned according to ISO 1110

	Condition	Standard	Unit	Value
Thermal properties				
Melting temperature, 10°C/min		ISO 11357-1	°C	262

	Condition	Standard	Unit	Value
Burning behaviour				
Flammability, 0.75 mm	0.75 mm	UL 94		HB
Burning rate, FMVSS, Thickness 1 mm		FMVSS 302		< 100 mm/min

	Condition	Standard	Unit	Value
Electrical properties				
Volume resistivity		IEC 62631-3-1	ohm.m	1.0E13
Surface resistivity		IEC 62631-3-1	ohm	1.0E13

Processing conditions

Drying temperature/time	75-85°C / 2-4h (with dew point of dried air < -30 °C)
-------------------------	---

Processing conditions

Recommended melt temperature	270 - 290 °C
Recommended mould temperature	90 - 110 °C

Injection notes

The material is supplied in airtight bags, ready for use.,In case that the virgin material has absorbed moisture, it must be dried with a dehumidified air drying equipment, dew point minimum -20°C.,Recommended time 2-4h.

Injection advice

For reinforced polyamides, Domo recommends the use of steel with a high content of carbon, and purified for polishing, to avoid or limit the abrasion. For example: X38CrMoV5-1 (EN Norm) - 1.2367 /1.2343 (DIN Norm) or X160CrMoV12 (EN Norm) - 1.2601 /1.2379 (DIN Norm). In the case of high requirements on surface quality a mould temperature of up to 120°C can be considered.,The processing parameters like processing temperatures are a recommendation and can be adjusted in function of injection machine size, part geometry / design.