

TECHNICAL DATA SHEET

TECHNYL A 218HP V30 BK 21N

TECHNYL A 218HP V30 BK 21N is a polyamide 6.6, reinforced with 30% of glass fiber, heat stabilized, for injection moulding. This grade is designed to offer a long term heat resistance and is suitable to work in environments characterized by a very high temperature. (200°C)

General

Polymer type	PA66
Certifications	RoHS EC 1907/2006 (REACH)
Feature	heat-aging stabilized heat resistant
Applications	automotive applications
Colors available	black
Forms	pellets
Processing technology	injection moulding

Product identification

ISO 1043 abbreviation	PA66-GF30
-----------------------	-----------

Condition	Standard	Unit	Value
-----------	----------	------	-------

Physical properties

	Condition	Standard	Unit	Value
Density		ISO 1183	g/cm ³	1.35
Molding shrinkage, parallel		ISO 294-4, 2577	%	0.35
Molding shrinkage, normal		ISO 294-4, 2577	%	1.0

	Condition	Standard	Unit	Value
Mechanical properties				dam / cond.*
Tensile modulus	1 mm/min	ISO 527-1/-2	MPa	10000 / 6600
Stress at break		ISO 527-1/-2	MPa	170 / 110
Strain at break		ISO 527-1/-2	%	2.6 / 6.5
Flexural modulus, ISO 178	2 mm/min	ISO 178	MPa	9000 / 5900
Flexural strength, ISO 178	2 mm/min	ISO 178	MPa	260 / 180
Charpy impact strength, +23°C	+23°C	ISO 179/1eU	kJ/m ²	78 / 77
Charpy notched impact strength, +23°C	+23°C	ISO 179/1eA	kJ/m ²	14 / 18

*: **conditioned according to ISO 1110**

	Condition	Standard	Unit	Value
Thermal properties				
Melting temperature, 10°C/min		ISO 11357-1	°C	262
Temp. of deflection under load, 0.45 MPa	0.45 MPa	ISO 75	°C	258
Temp. of deflection under load, 1.80 MPa	1.80 MPa	ISO 75	°C	245

Processing conditions

Drying temperature/time	80 °C
Suggested max moisture	0.2 %
Rear temperature	270 - 280 °C
Middle temperature	275 - 285 °C
Front temperature	280 - 290 °C
Recommended mould temperature	70 - 100 °C

Injection notes

The material is supplied in airtight bags, ready for use. In case that the virgin material has absorbed moisture, it must be dried with a dehumidified air drying equipment, dew point minimum -20°C. Recommended time 2-4h.

Injection advice

For reinforced polyamides, Domo recommends the use of steel with a high content of carbon, and purified for polishing, to

TECHNYL®

DOMO
caring is our formula

TECHNICAL DATA SHEET

TECHNYL A 218HP V30 BK 21N

Injection advice

avoid or limit the abrasion. For example: X38CrMoV5-1 (EN Norm) - 1.2367 /1.2343 (DIN Norm) or X160CrMoV12 (EN Norm) - 1.2601 /1.2379 (DIN Norm). In the case of high requirements on surface quality a mould temperature of up to 120°C can be considered.,The processing parameters like processing temperatures are a recommendation and can be adjusted in function of injection machine size, part geometry / design.