

TECHNYL® PROTECT

Flame retardants

DOMO

caring is our formula

TECHNICAL DATA SHEET

TECHNYL PROTECT A 20 V25 BK 25

TECHNYL A 20 V25 BLACK 25



TECHNYL PROTECT A 20 V25 BK 25 is a Red Phosphorous flame retardant polyamide 66, reinforced with 25% of glass fiber, heat stabilized, for injection moulding. This grade provides robust UL 94 V-0 and a full UL yellow card while offering good mechanical properties. This grade is suitable for moulding insulating parts for electrical devices, and more generally for thin parts under stress.

General

Certifications	RoHS EC 1907/2006 (REACH)	UL listed product
Polymer type	PA66	
Feature	heat-aging stabilized UL 94 V0	red phosphorous flame retardant halogen free flame retardant
Applications	electrical/electronic applications	wire / cable applications
Colors available	black	natural
Forms	pellets	
Processing technology	injection moulding	

Product identification

ISO 1043 abbreviation	PA66-GF25 FR(52)
ISO 16396 designation	PA66,GF25FR(52),MH,S14-080

Condition	Standard	Unit	Value
-----------	----------	------	-------

Physical properties

Property	Condition	Standard	Unit	Value
Density		ISO 1183	g/cm ³	1.38
Water absorption	24 hr, 23°C	ISO 62	%	0.7 - 0.8
Molding shrinkage, parallel		ISO 294-4, 2577	%	0.35
Molding shrinkage, normal		ISO 294-4, 2577	%	1.2

	Condition	Standard	Unit	Value
Mechanical properties				dam / cond.*
Tensile modulus	1 mm/min	ISO 527-1/-2	MPa	9400 / 6300
Stress at break		ISO 527-1/-2	MPa	150 / 100
Strain at break		ISO 527-1/-2	%	2.5 / 5.2
Flexural modulus, ISO 178	2 mm/min	ISO 178	MPa	8500 / 5700
Flexural strength, ISO 178	2 mm/min	ISO 178	MPa	255 / 170
Charpy impact strength, +23°C	+23°C	ISO 179/1eU	kJ/m ²	55 / 60
Charpy impact strength, -30°C	-30°C	ISO 179/1eU	kJ/m ²	50 / -
Charpy notched impact strength, +23°C	+23°C	ISO 179/1eA	kJ/m ²	8 / 9
Charpy notched impact strength, -30°C	-30°C	ISO 179/1eA	kJ/m ²	7 / -
Izod notched impact strength, +23°C	+23°C	ISO 180/1A	kJ/m ²	8 / 9

*: **conditioned according to ISO 1110**

	Condition	Standard	Unit	Value
Thermal properties				
Melting temperature, 10°C/min		ISO 11357-1	°C	263
Temp. of deflection under load, 1.80 MPa	1.80 MPa	ISO 75	°C	244

Condition	Standard	Unit	Value
-----------	----------	------	-------

Burning behaviour

UL Yellow Card availability 1	Click here to have access to the UL Yellow Card availability 1 -> QMFZ2.E44716			
Flammability, 0.75 mm	0.75 mm	UL 94		V0
Flammability, 1.5 mm	1.5 mm	UL 94		V0
Flammability, 3.0 mm	3.0 mm	UL 94		V0
Glow-wire flammability index, GWFI, 0.75 mm	0.75 mm	IEC 60695-2-12	°C	960
Glow-wire flammability index, GWFI, 1.5 mm	1.5 mm	IEC 60695-2-12	°C	960
Glow-wire flammability index, GWFI, 3.0 mm			°C	960
Glow-wire ignition temperature, GWIT, 1.5 mm	1.5 mm	IEC 60695-2-13	°C	725
Oxygen index			%	31.0
Burning rate, FMVSS, Thickness 1 mm		FMVSS 302		< 100mm/min

Condition	Standard	Unit	Value
-----------	----------	------	-------

Electrical properties

Volume resistivity		IEC 62631-3-1	ohm.m	1.0E13
Surface resistivity		IEC 62631-3-1	ohm	1.0E13
Comparative tracking index	Solution A	IEC 60112	V	400.0
CTI performance level category		Sol A		PLC 1
Dielectric strength	1 mm	IEC 60243-1	kV/mm	30.0

Processing conditions

Drying temperature/time	80 °C
Suggested max moisture	0.2 %
Rear temperature	265 - 275 °C
Middle temperature	270 - 280 °C

Processing conditions

Front temperature	280 - 290 °C
Recommended mould temperature	60 - 90 °C

Injection notes

The material is supplied in airtight bags, ready for use.,In case that the virgin material has absorbed moisture, it must be dried with a dehumidified air drying equipment, dew point minimum -20°C.,Recommended time 2-4h.

Injection advice

All reinforced, flame retardant compounds generate some level of abrasion/corrosion to the steel processing equipment. These issues may be magnified by using incorrect processing conditions (temperatures, residence time, moisture level ...) during the moulding process. Therefore, Domo recommends you adhere to the processing conditions detailed in this technical data sheet. For equipment that comes into contact with molten flame retardant compounds, Domo advises you to use a steel with high chromium and high carbon content (having a minimum concentration of 16% chromium) to prevent corrosion and abrasion. For the correct reference of steel associated to flame retardant compounds' processing, please refer to your equipment manufacturers. In the case of high requirements on surface quality a mould temperature of up to 120°C can be considered.,The processing parameters like processing temperatures are a recommendation and can be adjusted in function of injection machine size, part geometry / design.