

TECHNICAL DATA SHEET

TECHNYL PROTECT A 50H1 BK

TECHNYL A 50H1 BLACK



TECHNYL PROTECT A 50H1 BK is an unreinforced polyamide 66 based on a non-phosphorous and non-halogenated flame retardant system, heat stabilized, for injection moulding. This flame retardant grade, offers excellent filling qualities combined with good stiffness.

General

Certifications	RoHS EC 1907/2006 (REACH)	UL listed product EN 45545
Polymer type	PA66	
Feature	halogen free flame retardant	
Applications	connectors	electrical/electronic applications
Colors available	black	natural
Forms	pellets	
Processing technology	injection moulding	

Product identification

ISO 1043 abbreviation	PA66 FR(30)
-----------------------	-------------

Condition	Standard	Unit	Value
-----------	----------	------	-------

Physical properties

Condition	Standard	Unit	Value
Density	ISO 1183	g/cm ³	1.16
Humidity absorption	T=23°C, 50% RH (equivalent ISO 1110)	%	2.6
Water absorption	24 hr, 23°C, immersion in water, thickness 2mm	%	0.9 - 1.0
Molding shrinkage, parallel	ISO 294-4, 2577	%	1.2 - 1.4
Molding shrinkage, normal	ISO 294-4, 2577	%	0.85 - 1.05

	Condition	Standard	Unit	Value
Mechanical properties				dam / cond.*
Tensile modulus	1 mm/min	ISO 527-1/-2	MPa	3800 / 1700
Stress at break		ISO 527-1/-2	MPa	75 / 50
Strain at break		ISO 527-1/-2	%	5 / 60
Flexural modulus, ISO 178	2 mm/min	ISO 178	MPa	3700 / 1000
Flexural modulus, ASTM D790	2 mm/min	ASTM D790	MPa	3800 / 1750
Flexural strength, ISO 178	2 mm/min	ISO 178	MPa	130 / 50
Flexural strength, ASTM D790	2 mm/min	ASTM D790	MPa	120 / 50
Charpy impact strength, +23°C	+23°C	ISO 179/1eU	kJ/m ²	80 / NB
Charpy impact strength, -30°C	-30°C	ISO 179/1eU	kJ/m ²	80 / -
Charpy notched impact strength, +23°C	+23°C	ISO 179/1eA	kJ/m ²	3.5 / 10
Charpy notched impact strength, -30°C	-30°C	ISO 179/1eA	kJ/m ²	3 / -
Izod notched impact strength, +23°C	+23°C	ISO 180/1A	kJ/m ²	3 / -

*: **conditioned according to ISO 1110**

	Condition	Standard	Unit	Value
Thermal properties				
Melting temperature, 10°C/min		ISO 11357-1	°C	263
Temp. of deflection under load, 0.45 MPa	0.45 MPa	ISO 75	°C	237
Temp. of deflection under load, 1.80 MPa	1.80 MPa	ISO 75	°C	85

Condition	Standard	Unit	Value
-----------	----------	------	-------

Burning behaviour

UL Yellow Card availability 1	Click here to have access to the UL Yellow Card availability 1 -> QMFZ2.E44716			
UL Yellow Card availability 2	Click here to have access to the UL Yellow Card availability 2 -> QMFZ2.E44716			
Flammability, 0.40 mm	0.40 mm	UL 94		V0
Flammability, 0.75 mm	0.75 mm	UL 94		V0
Flammability, 1.5 mm	1.5 mm	UL 94		V0
Flammability, 3.0 mm	3.0 mm	UL 94		V0
Glow-wire flammability index, GWFI, 0.75 mm	0.75 mm	IEC 60695-2-12	°C	960
Glow-wire flammability index, GWFI, 1.5 mm	1.5 mm	IEC 60695-2-12	°C	960
Glow-wire flammability index, GWFI, 3.0 mm			°C	960
Glow-wire ignition temperature, GWIT, 0.40 mm	0.40 mm	IEC 60695-2-13	°C	960
Glow-wire ignition temperature, GWIT, 0.75 mm	0.75 mm	IEC 60695-2-13	°C	960
Glow-wire ignition temperature, GWIT, 1.5 mm	1.5 mm	IEC 60695-2-13	°C	775
Oxygen index			%	33.0

Condition	Standard	Unit	Value
-----------	----------	------	-------

Electrical properties

Volume resistivity		IEC 62631-3-1	ohm.m	3.0E13
Surface resistivity		IEC 62631-3-1	ohm	3.0E15
Comparative tracking index	Solution A	IEC 60112	V	600.0
CTI performance level category		Sol A		PLC 0
Dielectric strength	1 mm	IEC 60243-1	kV/mm	21.0

Processing conditions

Drying temperature/time	80 °C
Suggested max moisture	0.15 %
Rear temperature	260 - 270 °C
Middle temperature	265 - 275 °C
Front temperature	265 - 275 °C
Recommended mould temperature	60 - 80 °C

Injection notes

The material is supplied in airtight bags, ready for use.,In case that the virgin material has absorbed moisture, it must be dried with a dehumidified air drying equipment, dew point minimum -20°C.,Recommended time 2-4h.

Injection advice

All reinforced, flame retardant compounds generate some level of abrasion/corrosion to the steel processing equipment. These issues may be magnified by using incorrect processing conditions (temperatures, residence time, moisture level ...) during the moulding process. Therefore, Domo recommends you adhere to the processing conditions detailed in this technical data sheet. For equipment that comes into contact with molten flame retardant compounds, Domo advises you to use a steel with high chromium and high carbon content (having a minimum concentration of 16% chromium) to prevent corrosion and abrasion. For the correct reference of steel associated to flame retardant compounds' processing, please refer to your equipment manufacturers. In the case of high requirements on surface quality a mould temperature of up to 120°C can be considered.,The processing parameters like processing temperatures are a recommendation and can be adjusted in function of injection machine size, part geometry / design.