

TECHNICAL DATA SHEET

TECHNYL PROTECT A 60G1 V25 NC
DOMAMID FR 66G25V0E NC



TECHNYL PROTECT A 60G1 V25 NC is a polyamide 66 based on a non-halogenated flame retardant system, reinforced with 25% of glass fiber, heat stabilized, for injection molding. This grade offers excellent flame retardancy properties (UL 94, 5VA, GWIT) combined with excellent processing, mechanical and electrical performance.

General

Certifications	RoHS EC 1907/2006 (REACH)	UL listed product
Polymer type	PA66	
Feature	halogen and red phosphorus free flame retardant UL 94 V0	heat-aging stabilized GWFI 960°C
Applications	electrical/electronic applications	
Colors available	black grey	natural white
Forms	pellets	
Processing technology	injection moulding	

Product identification

ISO 1043 abbreviation	PA66-GF25 FR(40)
ISO 16396 designation	PA66,GF25FR(40),MH,S14-090

Condition	Standard	Unit	Value
-----------	----------	------	-------

Physical properties

Density		ISO 1183	g/cm ³	1.38
Humidity absorption	T=23°C, 50% RH	ISO 62	%	1.7 - 1.8
Water absorption	24 hr, 23°C	ISO 62	%	1.1 - 1.2
Water absorption, saturation			%	5.6

	Condition	Standard	Unit	Value
Mechanical properties				dam / cond.*
Tensile modulus	1 mm/min	ISO 527-1/-2	MPa	10700 / 7500
Stress at break		ISO 527-1/-2	MPa	145 / 95
Strain at break		ISO 527-1/-2	%	2.5 / 3.3
Flexural modulus, ISO 178	2 mm/min	ISO 178	MPa	6600 / -
Flexural strength, ISO 178	2 mm/min	ISO 178	MPa	215 / -
Charpy impact strength, +23°C	+23°C	ISO 179/1eU	kJ/m ²	60 / 68

***: conditioned according to ISO 1110**

	Condition	Standard	Unit	Value
Thermal properties				
Melting temperature, 10°C/min		ISO 11357-1	°C	263
Temp. of deflection under load, 0.45 MPa	0.45 MPa	ISO 75	°C	259
Temp. of deflection under load, 1.80 MPa	1.80 MPa	ISO 75	°C	235
Vicat softening temperature	50°C/h - 50N	ISO 306	°C	245

Condition	Standard	Unit	Value
-----------	----------	------	-------

Burning behaviour

UL Yellow Card availability 1	Click here to have access to the UL Yellow Card availability 1 -> YC E44716			
Flammability, 0.40 mm	0.40 mm	UL 94		V0
Flammability, 0.75 mm	0.75 mm	UL 94		V0
Flammability, 1.5 mm	1.5 mm	UL 94		V0,5VA
Flammability, 3.0 mm	3.0 mm	UL 94		V0,5VA
Glow-wire flammability index, GWFI, 0.40 mm	0.40 mm	IEC 60695-2-12	°C	960
Glow-wire flammability index, GWFI, 0.75 mm	0.75 mm	IEC 60695-2-12	°C	960
Glow-wire flammability index, GWFI, 1.5 mm	1.5 mm	IEC 60695-2-12	°C	960
Glow-wire flammability index, GWFI, 3.0 mm			°C	960
Glow-wire ignition temperature, GWIT, 0.40 mm	0.40 mm	IEC 60695-2-13	°C	750
Glow-wire ignition temperature, GWIT, 0.75 mm	0.75 mm	IEC 60695-2-13	°C	750
Glow-wire ignition temperature, GWIT, 1.5 mm	1.5 mm	IEC 60695-2-13	°C	775
Glow-wire ignition temperature, GWIT, 3.0 mm	3.0 mm	IEC 60695-2-13	°C	800
Oxygen index			%	33.0
Burning rate, FMVSS, Thickness 1 mm		FMVSS 302		< 100mm/min

Condition	Standard	Unit	Value
-----------	----------	------	-------

Electrical properties

Volume resistivity		IEC 62631-3-1	ohm.m	6.0E12
Surface resistivity		IEC 62631-3-1	ohm	2.0E15
Comparative tracking index	Solution A	IEC 60112	V	600.0
CTI performance level category		Sol A		PLC 1

Processing conditions

Drying temperature/time	80°C
Suggested max moisture	0.15 %
Rear temperature	265 - 275 °C
Middle temperature	265 - 275 °C
Front temperature	270 - 280 °C
Recommended mould temperature	60 - 80 °C

Injection notes

The material is supplied in airtight bags, ready for use.,In case that the virgin material has absorbed moisture, it must be dried with a dehumidified air drying equipment, dew point minimum -20°C.,Recommended time 2-4h.

Injection advice

All reinforced, flame retardant compounds generate some level of abrasion/corrosion to the steel processing equipment. These issues may be magnified by using incorrect processing conditions (temperatures, residence time, moisture level ...) during the moulding process. Therefore, Domo recommends you adhere to the processing conditions detailed in this technical data sheet. For equipment that comes into contact with molten flame retardant compounds, Domo advises you to use a steel with high chromium and high carbon content (having a minimum concentration of 16% chromium) to prevent corrosion and abrasion. For the correct reference of steel associated to flame retardant compounds' processing, please refer to your equipment manufacturers. In the case of high requirements on surface quality a mould temperature of up to 120°C can be considered.,The processing parameters like processing temperatures are a recommendation and can be adjusted in function of injection machine size, part geometry / design.