

TECHNICAL DATA SHEET

TECHNYL PROTECT A 60G1 V25 GY 2622



TECHNYL PROTECT A 60G1 V25 GY 26223 is a polyamide 66 based on a non-halogenated flame retardant system, reinforced with 25% of glass fiber, heat stabilized, for injection molding. This grade offers excellent flame retardancy properties (UL 94, 5VA, GWIT) combined with excellent processing, mechanical and electrical performance.

General

| | | |
|-----------------------|--|-------------------------------------|
| Certifications | RoHS EC 1907/2006 (REACH) | UL listed product EN 45545 |
| Polymer type | PA66 | |
| Feature | halogen and red phosphorus free flame retardant UL 94 V0 | heat-aging stabilized GWFI 960°C |
| Applications | electrical/electronic applications | |
| Colors available | black grey | natural white |
| Forms | pellets | |
| Processing technology | injection moulding | |

Product identification

| | |
|-----------------------|----------------------------|
| ISO 1043 abbreviation | PA66-GF25 FR(40) |
| ISO 16396 designation | PA66,GF25FR(40),MH,S14-090 |

| Condition | Standard | Unit | Value |
|-----------|----------|------|-------|
|-----------|----------|------|-------|

Physical properties

| | Condition | Standard | Unit | Value |
|------------------------------|-------------------|----------|-------------------|-----------|
| Density | | ISO 1183 | g/cm ³ | 1.38 |
| Humidity absorption | T=23°C, 50% RH | ISO 62 | % | 1.7 - 1.8 |
| Water absorption | 24 hr, 23°C | ISO 62 | % | 0.7 - 0.8 |
| Water absorption, saturation | | | % | 4.4 |

| | Condition | Standard | Unit | Value |
|-------------------------------|-----------|--------------|-------------------|---------------------|
| Mechanical properties | | | | dam / cond.* |
| Tensile modulus | 1 mm/min | ISO 527-1/-2 | MPa | 10000 / 7000 |
| Stress at break | | ISO 527-1/-2 | MPa | 120 / 80 |
| Strain at break | | ISO 527-1/-2 | % | 1.8 / 2.4 |
| Flexural modulus, ISO 178 | 2 mm/min | ISO 178 | MPa | 6300 / 4250 |
| Flexural strength, ISO 178 | 2 mm/min | ISO 178 | MPa | 180 / 135 |
| Charpy impact strength, +23°C | +23°C | ISO 179/1eU | kJ/m ² | 35 / 38 |

***: conditioned according to ISO 1110**

| | Condition | Standard | Unit | Value |
|--|--------------|-------------|------|-------|
| Thermal properties | | | | |
| Melting temperature, 10°C/min | | ISO 11357-1 | °C | 263 |
| Temp. of deflection under load, 0.45 MPa | 0.45 MPa | ISO 75 | °C | 259 |
| Temp. of deflection under load, 1.80 MPa | 1.80 MPa | ISO 75 | °C | 235 |
| Vicat softening temperature | 50°C/h - 50N | ISO 306 | °C | 245 |

| Condition | Standard | Unit | Value |
|-----------|----------|------|-------|
|-----------|----------|------|-------|

Burning behaviour

| | | | | |
|---|---|----------------|----|-------------|
| UL Yellow Card availability 1 | Click here to have access to the UL Yellow Card availability 1 -> YC A 60G1 V25 | | | |
| Glow-wire flammability index, GWFI, 0.40 mm | 0.40 mm | IEC 60695-2-12 | °C | 960 |
| Glow-wire flammability index, GWFI, 0.75 mm | 0.75 mm | IEC 60695-2-12 | °C | 960 |
| Glow-wire flammability index, GWFI, 1.5 mm | 1.5 mm | IEC 60695-2-12 | °C | 960 |
| Glow-wire flammability index, GWFI, 3.0 mm | | | °C | 960 |
| Glow-wire ignition temperature, GWIT, 0.40 mm | 0.40 mm | IEC 60695-2-13 | °C | 750 |
| Glow-wire ignition temperature, GWIT, 0.75 mm | 0.75 mm | IEC 60695-2-13 | °C | 750 |
| Glow-wire ignition temperature, GWIT, 1.5 mm | 1.5 mm | IEC 60695-2-13 | °C | 775 |
| Glow-wire ignition temperature, GWIT, 3.0 mm | 3.0 mm | IEC 60695-2-13 | °C | 800 |
| Burning rate, FMVSS, Thickness 1 mm | | FMVSS 302 | | <100 mm/min |

| Condition | Standard | Unit | Value |
|-----------|----------|------|-------|
|-----------|----------|------|-------|

Electrical properties

| | | | | |
|--------------------------------|------------|---------------|-------|--------|
| Volume resistivity | | IEC 62631-3-1 | ohm.m | 6.0E12 |
| Surface resistivity | | IEC 62631-3-1 | ohm | 2.0E15 |
| Comparative tracking index | Solution A | IEC 60112 | V | 600.0 |
| CTI performance level category | | Sol A | | PLC 0 |
| Dielectric strength | 1 mm | IEC 60243-1 | kV/mm | 35.0 |

Processing conditions

| | |
|------------------------|--------------|
| Suggested max moisture | 0.15 % |
| Rear temperature | 265 - 275 °C |
| Middle temperature | 265 - 275 °C |

Processing conditions

| | |
|-------------------------------|--------------|
| Front temperature | 270 - 280 °C |
| Recommended mould temperature | 60 - 80 °C |

Injection notes

The material is supplied in airtight bags, ready for use. In case that the virgin material has absorbed moisture, it must be dried with a dehumidified air drying equipment, dew point minimum -20°C. Recommended time 2-4h.

Injection advice

All reinforced, flame retardant compounds generate some level of abrasion/corrosion to the steel processing equipment. These issues may be magnified by using incorrect processing conditions (temperatures, residence time, moisture level ...) during the moulding process. Therefore, Domo recommends you adhere to the processing conditions detailed in this technical data sheet. For equipment that comes into contact with molten flame retardant compounds, Domo advises you to use a steel with high chromium and high carbon content (having a minimum concentration of 16% chromium) to prevent corrosion and abrasion. For the correct reference of steel associated to flame retardant compounds' processing, please refer to your equipment manufacturers. In the case of high requirements on surface quality a mould temperature of up to 120°C can be considered. The processing parameters like processing temperatures are a recommendation and can be adjusted in function of injection machine size, part geometry / design.