

TECHNICAL DATA SHEET

## TECHNYL AR 218 V50 BK

TECHNYL AR 218 V50 BK is a polyamide 66, reinforced with 50% of glass fibre, heat stabilized, for injection moulding. This grade offers a good combination between thermal and mechanical properties.

### General

Certifications	RoHS	EC 1907/2006 (REACH)
Polymer type	PA66	
Feature	heat-aging stabilized	high stiffness
Applications	small appliance	general purpose
Colors available	black	
Forms	pellets	
Processing technology	injection moulding	

### Product identification

ISO 1043 abbreviation	PA66-GF50
ISO 16396 designation	PA66-GF50,MH,S14-150

Condition	Standard	Unit	Value
-----------	----------	------	-------

### Physical properties

	Condition	Standard	Unit	Value
Density		ISO 1183	g/cm <sup>3</sup>	1.56
Water absorption	24 hr, 23°C	ISO 62	%	0.7

	Condition	Standard	Unit	Value
<b>Mechanical properties</b>				<b>dam / cond.*</b>
Tensile modulus	1 mm/min	ISO 527-1/-2	MPa	15000 / 11000
Stress at break		ISO 527-1/-2	MPa	205 / 140
Strain at break		ISO 527-1/-2	%	2 / 4
Flexural modulus, ISO 178	2 mm/min	ISO 178	MPa	14500 / -
Flexural strength, ISO 178	2 mm/min	ISO 178	MPa	330 / -
Charpy impact strength, +23°C	+23°C	ISO 179/1eU	kJ/m <sup>2</sup>	70 / 80
Charpy notched impact strength, +23°C	+23°C	ISO 179/1eA	kJ/m <sup>2</sup>	13 / 14
Izod impact strength, +23°C	+23°C	ISO 180/1U	kJ/m <sup>2</sup>	70 / -
Izod notched impact strength, +23°C	+23°C	ISO 180/1A	kJ/m <sup>2</sup>	18 / -

\*: **conditioned according to ISO 1110**

	Condition	Standard	Unit	Value
<b>Thermal properties</b>				
Melting temperature, 10°C/min		ISO 11357-1	°C	262
Temp. of deflection under load, 0.45 MPa	0.45 MPa	ISO 75	°C	260
Temp. of deflection under load, 1.80 MPa	1.80 MPa	ISO 75	°C	250

	Condition	Standard	Unit	Value
<b>Burning behaviour</b>				
Burning rate, FMVSS, Thickness 1 mm		FMVSS 302		< 100 mm/min


<b>Processing conditions</b>	
Drying temperature/time	80 °C
Suggested max moisture	0.2 %
Rear temperature	270 - 280 °C
Middle temperature	280 - 290 °C
Front temperature	280 - 300 °C

## Processing conditions

Recommended mould temperature	70 - 100 °C
-------------------------------	-------------


**Stress-strain, dry**

Temperature (°C)



**Stress-strain, conditioned**

Temperature (°C)



## Injection notes

The material is supplied in airtight bags, ready for use. In case that the virgin material has absorbed moisture, it must be dried with a dehumidified air drying equipment, dew point minimum -20°C. Recommended time 2-4h.

## Injection advice

For reinforced polyamides, Domo recommends the use of steel with a high content of carbon, and purified for polishing, to avoid or limit the abrasion. For example: X38CrMoV5-1 (EN Norm) - 1.2367 /1.2343 (DIN Norm) or X160CrMoV12 (EN Norm) - 1.2601 /1.2379 (DIN Norm). In the case of high requirements on surface quality a mould temperature of up to 120°C can be considered. The processing parameters like processing temperatures are a recommendation and can be adjusted in function of injection machine size, part geometry / design.