

TECHNICAL DATA SHEET

## TECHNYL PURE A 219E1 V33 BK

### TECHNYL A 219E1 V33 BLACK

TECHNYL PURE A 219E1 V33 BK is a polyamide PA66 reinforced with 33% of glass fibre, organic heat stabilized, for injection moulding. This grade offers an excellent combination between thermal and mechanical properties. This grade offers a formula clean from additive that contain halogen and other substances (ex: phosphorus) that can migrate and generate corrosion issues. < 50ppm halogen content guaranteed, based on internal elution analysis. Electrofriendly heat satbilized grade. Suitable for laser printing.

#### General

Polymer type	PA66		
Certifications	RoHS	EC 1907/2006 (REACH)	
Feature	lasermarkable organic heat stabilized	electro-friendly very high flow	
Applications	automotive applications fuel cell / H2 system	connectors	
Colors available	black		
Forms	pellets		
Processing technology	injection moulding		

#### Product identification

ISO 1043 abbreviation	PA66-G33
-----------------------	----------

Condition	Standard	Unit	Value
-----------	----------	------	-------

#### Physical properties

	Condition	Standard	Unit	Value
Density		ISO 1183	g/cm <sup>3</sup>	1.4
Water absorption	24 hr, 23°C	ISO 62	%	0.78
Molding shrinkage, parallel		ISO 294-4, 2577	%	0.28
Molding shrinkage, normal		ISO 294-4, 2577	%	0.98

	Condition	Standard	Unit	Value
<b>Mechanical properties</b>				<b>dam / cond.*</b>
Tensile modulus	1 mm/min	ISO 527-1/-2	MPa	11000 / -
Stress at break		ISO 527-1/-2	MPa	200 / -
Strain at break		ISO 527-1/-2	%	2.8 / -
Flexural modulus, ISO 178	2 mm/min	ISO 178	MPa	9200 / -
Flexural modulus, ASTM D790	2 mm/min	ASTM D790	MPa	10600 / -
Flexural strength, ISO 178	2 mm/min	ISO 178	MPa	190 / -
Flexural strength, ASTM D790	2 mm/min	ASTM D790	MPa	270 / -
Charpy impact strength, +23°C	+23°C	ISO 179/1eU	kJ/m <sup>2</sup>	70 / -
Charpy notched impact strength, +23°C	+23°C	ISO 179/1eA	kJ/m <sup>2</sup>	13 / -
Izod impact strength, +23°C	+23°C	ISO 180/1U	kJ/m <sup>2</sup>	65 / -
Izod notched impact strength, +23°C	+23°C	ISO 180/1A	kJ/m <sup>2</sup>	12 / -

\*: **conditioned according to ISO 1110**

	Condition	Standard	Unit	Value
<b>Thermal properties</b>				
Melting temperature, 10°C/min		ISO 11357-1	°C	263
Temp. of deflection under load, 1.80 MPa	1.80 MPa	ISO 75	°C	255

<b>Processing conditions</b>	
Drying temperature/time	80 °C
Suggested max moisture	0.2 %
Rear temperature	270 - 280 °C
Middle temperature	275 - 285 °C
Front temperature	280 - 290 °C
Recommended mould temperature	70 - 100 °C

# TECHNYL®

**DOMO**  
caring is our formula

TECHNICAL DATA SHEET

TECHNYL PURE A 219E1 V33 BK

## Injection notes

The material is supplied in airtight bags, ready for use. In case that the virgin material has absorbed moisture, it must be dried with a dehumidified air drying equipment, dew point minimum -20°C. Recommended time 2-4h.

## Injection advice

For reinforced polyamides, Domo recommends the use of steel with a high content of carbon, and purified for polishing, to avoid or limit the abrasion. For example: X38CrMoV5-1 (EN Norm) - 1.2367 / 1.2343 (DIN Norm) or X160CrMoV12 (EN Norm) - 1.2601 / 1.2379 (DIN Norm). In the case of high requirements on surface quality a mould temperature of up to 120°C can be considered. The processing parameters like processing temperatures are a recommendation and can be adjusted in function of injection machine size, part geometry / design.