

TECHNICAL DATA SHEET

TECHNYL D 218CR V50 BK

TECHNYL eXten D 218CR V50 BLACK

TECHNYL D 218CR V50 BK is a high glass reinforced grade based on polyamide blend of polyamide 6.10 and polyamide 66, heat stabilized, for injection moulding. This grade shows outstanding resistance to hydrolysis, very low water uptake, enhanced dimension stability and chemical resistance to long life automotive coolants. It also offers an excellent crack resistance to calcium chloride road salts, good injection process ability, high surface aspect quality, and overall high thermo-mechanical properties.

General

Polymer type	PA610 + PA66 blend	
Certifications	RoHS	EC 1907/2006 (REACH)
Feature	heat-aging stabilized chemical resistant excellent glycol resistant good surface finish road salt resistant	hydrolysis stabilized contains renewable content excellent hydrolysis resistant low moisture absorption
Applications	automotive applications	
Colors available	black	
Forms	pellets	
Processing technology	injection moulding	

Product identification

ISO 1043 abbreviation	PA610+PA66-GF50
ISO 16396 designation	PA610+PA66,GF50,MHW,S14-160

Condition	Standard	Unit	Value
-----------	----------	------	-------

Physical properties

Condition	Standard	Unit	Value	
Density	ISO 1183	g/cm ³	1.54	
Humidity absorption	T=23 ^o C, 50% RH	ISO 62	%	1.1
Water absorption	24 hr, 23 ^o C	ISO 62	%	0.45 - 0.5
Molding shrinkage, parallel	ISO 294-4, 2577	%	0.3 - 0.5	
Molding shrinkage, normal	ISO 294-4, 2577	%	0.7 - 0.9	

	Condition	Standard	Unit	Value
Mechanical properties				dam / cond.*
Tensile modulus	1 mm/min	ISO 527-1/-2	MPa	16800 / 11600
Stress at break		ISO 527-1/-2	MPa	225 / 165
Strain at break		ISO 527-1/-2	%	3 / 5.1
Flexural modulus, ISO 178	2 mm/min	ISO 178	MPa	13600 / 9400
Flexural strength, ISO 178	2 mm/min	ISO 178	MPa	345 / 250

*: **conditioned according to ISO 1110**

	Condition	Standard	Unit	Value
Thermal properties				
Temp. of deflection under load, 1.80 MPa	1.80 MPa	ISO 75	°C	214

	Condition	Standard	Unit	Value
Burning behaviour				
Burning rate, FMVSS, Thickness 1 mm		FMVSS 302		<100 mm/min

Processing conditions

Drying temperature/time	80 °C / 4 h
Suggested max moisture	0.15 %
Rear temperature	280 °C
Middle temperature	290 °C
Front temperature	300 °C
Recommended mould temperature	100 °C

Injection notes

The material is supplied in airtight bags, ready for use. In case that the virgin material has absorbed moisture, it must be dried with a dehumidified air drying equipment, dew point minimum -20°C. Recommended time 2-4h.

Injection advice

For reinforced polyamides, Domo recommends the use of steel with a high content of carbon, and purified for polishing, to avoid or limit the abrasion. For example: X38CrMoV5-1 (EN Norm) - 1.2367 / 1.2343 (DIN Norm) or X160CrMoV12 (EN Norm) - DOMO Engineering Plastics

TECHNYL®

DOMO
caring is our formula

TECHNICAL DATA SHEET

TECHNYL D 218CR V50 BK

Injection advice

1.2601 /1.2379 (DIN Norm). In the case of high requirements on surface quality a mould temperature of up to 120°C can be considered.,The processing parameters like processing temperatures are a recommendation and can be adjusted in function of injection machine size, part geometry / design.