



## DOMAMID® 6AV

Polyamide 6, general purpose, for injection moulding.

TYPICAL PROPERTIES	CONDITION	STANDARD	UNIT	VALUE
<b>PHYSICAL</b>				
Density		ISO 1183	[g/cm <sup>3</sup> ]	1,14
Mold shrinkage parallel	72 hrs, 23°C, 50% RH	ISO 2577	[%]	0,9 ÷ 1,1
Mold shrinkage transverse	72 hrs, 23°C, 50% RH	ISO 2577	[%]	1,0 ÷ 1,2
<b>RHEOLOGICAL</b>				
Melt Volume Rate (MVR)	275 °C - 5,0 kg	ISO 1133	[cm <sup>3</sup> /10 min]	165
Viscosity number		ISO 307	[ml/g]	145
<b>MECHANICAL</b>				
				<b>dam / cond.*</b>
Tensile modulus	1 mm/min	ISO 527	[MPa]	3200 / 1000
Tensile strain at break	50 mm/min	ISO 527	[%]	40 / >50
Tensile stress at yield	50 mm/min	ISO 527	[MPa]	80 / 40
Flexural modulus	2 mm/min	ISO 178	[MPa]	2800 / 900
Flexural strength	2 mm/min	ISO 178	[MPa]	105 / 35
Charpy unnotched	+23 °C	ISO 179/1eU	[kJ/m <sup>2</sup> ]	NB / NB
Charpy notched	+23 °C	ISO 179/1eA	[kJ/m <sup>2</sup> ]	5 / -
Izod impact unnotched	+23 °C	ISO 180/1A	[kJ/m <sup>2</sup> ]	NB / NB
Izod impact notched	+23 °C	ISO 180/1A	[kJ/m <sup>2</sup> ]	5 / -
Hardness Rockwell		ISO 2039/2	[ScaleR]	120 / -
<b>THERMAL</b>				
Melting point	DSC	ISO 11357-1	[°C]	222
Heat Deflection Temperature (HDT-B)	0,45 MPa	ISO 75	[°C]	175
Heat Deflection Temperature (HDT-A)	1,80 MPa	ISO 75	[°C]	65
VICAT softening temperature	50°C/h - 50N	ISO 306	[°C]	200
<b>ELECTRICAL</b>				
Volume resistivity		IEC 93	[Ω·cm]	10 <sup>15</sup>
Surface resistivity		IEC 93	[Ω]	10 <sup>13</sup>
Comparative Tracking Index (CTI)	Solution A	IEC 112	[V]	600
<b>BURNING BEHAVIOUR</b>				
Flammability	0,8 mm	UL 94	[Class]	V2
Glow Wire Flammability Index (GWFI)	1 ÷ 3 mm	IEC 60695-2-12	[°C]	750÷850
Burning rate (FMVSS)		FMVSS 302	[mm/min]	< 100

Test run at 23°C if not differently specified, DAM state (dry as moulded), valid for natural colored products

\*: conditioned according to ISO 1110

### PROCESSING CONDITIONS:

Drying temperature/time	: 75÷85°C / 2÷4h
Recommended melt temperature	: 230÷250 °C
Recommended mould temperature	: 60÷90 °C