

TECHNICAL DATA SHEET

TECHNYL 4EARTH C2E 218 V35 BK H
ECONAMID FL 6G35H2 BK



Polyamide 6, 35% glass fiber reinforced, heat-aging stabilized, for injection moulding, black

General

Polymer type	PA6		
Certifications	RoHS	EC 1907/2006 (REACH)	
Feature	heat-aging stabilized	recycled	
Colors available	black		
Forms	pellets		
Processing technology	injection moulding		

Product identification

ISO 1043 abbreviation	PA6(REC)-GF35
ISO 16396 designation	PA6,GF35(R100),MH,S14-100

Condition	Standard	Unit	Value
-----------	----------	------	-------

Physical properties

Density		ISO 1183	g/cm ³	1.42
Humidity absorption	T=23°C, 50% RH	ISO 62	%	1.8 - 2.2
Water absorption	24 hr, 23°C	ISO 62	%	1.4 - 1.5
Water absorption, saturation			%	6.1
Molding shrinkage, parallel		ISO 294-4, 2577	%	0.25 - 0.45
Molding shrinkage, normal		ISO 294-4, 2577	%	0.75 - 0.95
Viscosity number	96% H2SO4	ISO 307	cm ³ /g	135.0

	Condition	Standard	Unit	Value
Mechanical properties				dam / cond.*
Tensile modulus	1 mm/min	ISO 527-1/-2	MPa	10500 / 5500
Stress at break	5 mm/min	ISO 527-1/-2	MPa	150 / 90
Strain at break	5 mm/min	ISO 527-1/-2	%	2.5 / 6
Flexural modulus, ISO 178	2 mm/min	ISO 178	MPa	9000 / 5000
Flexural strength, ISO 178	2 mm/min	ISO 178	MPa	230 / 140
Charpy impact strength, +23°C	+23°C	ISO 179/1eU	kJ/m ²	62 / 75
Charpy impact strength, -30°C	-30°C	ISO 179/1eU	kJ/m ²	55 / 60
Charpy notched impact strength, +23°C	+23°C	ISO 179/1eA	kJ/m ²	9 / 19
Charpy notched impact strength, -30°C	-30°C	ISO 179/1eA	kJ/m ²	6 / 7

*: **conditioned according to ISO 1110**

	Condition	Standard	Unit	Value
Thermal properties				
Melting temperature, 10°C/min		ISO 11357-1	°C	221
Temp. of deflection under load, 0.45 MPa	0.45 MPa	ISO 75	°C	220
Temp. of deflection under load, 1.80 MPa	1.80 MPa	ISO 75	°C	210
Vicat softening temperature	50°C/h - 50N	ISO 306	°C	210

	Condition	Standard	Unit	Value
Burning behaviour				
Flammability		UL 94		HB
Burning rate, FMVSS, Thickness 1 mm		FMVSS 302		< 100 mm/min



Condition	Standard	Unit	Value
-----------	----------	------	-------

Electrical properties

Volume resistivity		IEC 62631-3-1	ohm.m	1.0E16
Surface resistivity		IEC 62631-3-1	ohm	1.0E14
Comparative tracking index	Solution A	IEC 60112	V	450.0
CTI performance level category		Sol A		PLC 1

Processing conditions

Drying temperature/time	75-85°C / 2-4h (with dew point of dried air < -30 °C)
Recommended melt temperature	250 - 290 °C
Recommended mould temperature	80 - 100 °C



Injection notes

The material is supplied in airtight bags, ready for use. In case that the virgin material has absorbed moisture, it must be dried with a dehumidified air drying equipment, dew point minimum -20°C. Recommended time 2-4h.

Injection advice

For reinforced polyamides, Domo recommends the use of steel with a high content of carbon, and purified for polishing, to avoid or limit the abrasion. For example: X38CrMoV5-1 (EN Norm) - 1.2367 /1.2343 (DIN Norm) or X160CrMoV12 (EN Norm) - 1.2601 /1.2379 (DIN Norm). In the case of high requirements on surface quality a mould temperature of up to 120°C can be considered. The processing parameters like processing temperatures are a recommendation and can be adjusted in function of injection machine size, part geometry / design.