

## TECHNICAL DATA SHEET

# TECHNYL C 116 V35 WT 1146

(Previously DOMAMID 6LVG35 WT91146)

Polyamide 6, 35% glass fiber reinforced, improved flowability, for injection moulding

### General

Feature	Improved flowability
Polymer type	PA6 (Polyamide 6)
Processing technology	Injection molding
Certification	RoHS

### Product identification

ISO 1043 abbreviation	PA6-GF35
ISO 16396 designation	PA6,GF35,M1,S12-110

	Condition	Standard	Unit	Value
<b>Physical properties</b>				
Density		ISO 1183	g/cm <sup>3</sup>	1.4
Molding shrinkage, parallel		ISO 294-4, 2577	%	0.2 - 0.4
Molding shrinkage, normal		ISO 294-4, 2577	%	0.8 - 1
Viscosity number	96% H2SO4	ISO 307	cm <sup>3</sup> /g	125

### Mechanical properties

				dam / cond.*
Tensile modulus	1 mm/min	ISO 527-1/-2	MPa	11000 / -
Stress at break	5 mm/min	ISO 527-1/-2	MPa	180 / -
Strain at break	5 mm/min	ISO 527-1/-2	%	3 / -
Flexural modulus, ISO 178	2 mm/min	ISO 178	MPa	9500 / -
Flexural strength, ISO 178	2 mm/min	ISO 178	MPa	265 / -
Charpy impact strength, +23°C	+23°C	ISO 179/1eU	kJ/m <sup>2</sup>	90 / -
Charpy notched impact strength, +23°C	+23°C	ISO 179/1eA	kJ/m <sup>2</sup>	15 / -
Izod impact strength, +23°C	+23°C	ISO 180/1U	kJ/m <sup>2</sup>	80 / -
Izod notched impact strength, +23°C	+23°C	ISO 180/1A	kJ/m <sup>2</sup>	15 / -

	Condition	Standard	Unit	Value
<b>Thermal properties</b>				
Melting temperature, 10°C/min		ISO 11357-1	°C	221
Temp. of deflection under load, 0.45 MPa	0.45 MPa	ISO 75	°C	215
Temp. of deflection under load, 1.80 MPa	1.80 MPa	ISO 75	°C	200
Vicat softening temperature	50°C/h - 50N	ISO 306	°C	210

### Electrical properties

Volume resistivity		IEC 62631-3-1	ohm.m	1E+013
Surface resistivity		IEC 62631-3-1	ohm	1E+013

### Burning behaviour

Flammability, 0.75 mm	0.75 mm	UL 94		HB
Burning rate, FMVSS, Thickness 1 mm		FMVSS 302		< 100 mm/min

*Test run at 23°C if not differently specified, DAM state (dry as moulded), valid for natural colored products.  
\*: conditioned according to ISO 1110*

### Processing conditions

Drying temperature/time	75-85°C / 2-4h (with dew point of dried air < -30 °C)			
Recommended melt temperature	240 - 270 °C			
Recommended mould temperature	90 - 100 °C			

*These parameters are typical of the product but should be related to the type of machinery used and to the type of moulded part.*