

TECHNICAL DATA SHEET

TECHNYL C 116 YL 1073 LP

DOMAMID 6LV 910

Polyamide 6, improved flowability, for injection moulding

General

Polymer type	PA6		
Certifications	RoHS EC 1907/2006 (REACH)	UL listed product	
Feature	improved flowability not heat stabilized	UL 94 V2	
Colors available	black	red	
Forms	pellets		
Processing technology	injection moulding		

Product identification

ISO 1043 abbreviation	PA6
ISO 16396 designation	PA6,M,S12-030

Condition	Standard	Unit	Value
-----------	----------	------	-------

Physical properties

Condition	Standard	Unit	Value	
Density	ISO 1183	g/cm ³	1.17	
Humidity absorption	T=23°C, 50% RH	ISO 62	%	3.2 - 3.3
Water absorption	24 hr, 23°C	ISO 62	%	1.9 - 2.0
Water absorption, saturation			%	9.1
Molding shrinkage, parallel	ISO 294-4, 2577	%		1.6 - 1.8
Molding shrinkage, normal	ISO 294-4, 2577	%		1.6 - 1.8
Viscosity number	96% H2SO4	ISO 307	cm ³ /g	135.0

	Condition	Standard	Unit	Value
Mechanical properties				dam / cond.*
Tensile modulus	1 mm/min	ISO 527-1/-2	MPa	3000 / -
Strain at break	50 mm/min	ISO 527-1/-2	%	25 / -
Yield stress	50 mm/min	ISO 527-1/-2	MPa	78 / -
Flexural modulus, ISO 178	2 mm/min	ISO 178	MPa	2600 / -
Flexural strength, ISO 178	2 mm/min	ISO 178	MPa	70 / -
Charpy notched impact strength, +23°C	+23°C	ISO 179/1eA	kJ/m ²	5.5 / -
Izod notched impact strength, +23°C	+23°C	ISO 180/1A	kJ/m ²	5 / -

*: **conditioned according to ISO 1110**

	Condition	Standard	Unit	Value
Thermal properties				
Melting temperature, 10°C/min		ISO 11357-1	°C	221

	Condition	Standard	Unit	Value
Burning behaviour				
UL Yellow Card availability 1	Click here to have access to the UL Yellow Card availability 1 -> E170540-100053880			
Flammability, 0.75 mm	0.75 mm	UL 94		V2
Flammability, 1.5 mm	1.5 mm	UL 94		V2
Flammability, 3.0 mm	3.0 mm	UL 94		V2
Burning rate, FMVSS, Thickness 1 mm		FMVSS 302		< 100 mm/min

	Condition	Standard	Unit	Value
Electrical properties				
Volume resistivity		IEC 62631-3-1	ohm.m	1.0E13
Surface resistivity		IEC 62631-3-1	ohm	1.0E13

Processing conditions

Drying temperature/time	75-85°C / 2-4h (with dew point of dried air < -30 °C)
Suggested max moisture	0.2 %
Rear temperature	230 - 235 °C
Middle temperature	235 - 240 °C
Front temperature	235 - 245 °C
Recommended melt temperature	230 - 245 °C
Recommended mould temperature	60 - 80 °C

Injection notes

The material is supplied in airtight bags, ready for use. In case that the virgin material has absorbed moisture, it must be dried with a dehumidified air drying equipment, dew point minimum -20°C. Recommended time 2-4h.

Injection advice

For reinforced polyamides, Domo recommends the use of steel with a high content of carbon, and purified for polishing, to avoid or limit the abrasion. For example: X38CrMoV5-1 (EN Norm) - 1.2367 /1.2343 (DIN Norm) or X160CrMoV12 (EN Norm) - 1.2601 /1.2379 (DIN Norm). In the case of high requirements on surface quality a mould temperature of up to 120°C can be considered. The processing parameters like processing temperatures are a recommendation and can be adjusted in function of injection machine size, part geometry / design.