

TECHNICAL DATA SHEET

## TECHNYL C 216 V30 GY 1869 CF

Polyamide 6, 30% glass fiber reinforced, for injection moulding

### General

Polymer type	PA6		
Certifications	RoHS	EC 1907/2006 (REACH)	
Applications	small appliance handles	home & office furniture power tool / garden equipment	
Colors available	black grey white	natural blue	
Forms	pellets		
Processing technology	injection moulding		

### Product identification

ISO 1043 abbreviation	PA6-GF30
ISO 16396 designation	PA6,GF30,M,S14-090

Condition	Standard	Unit	Value
-----------	----------	------	-------

### Physical properties

	Condition	Standard	Unit	Value
Density		ISO 1183	g/cm <sup>3</sup>	1.36
Humidity absorption	T=23°C, 50% RH	ISO 62	%	2.2 - 2.4
Water absorption	24 hr, 23°C	ISO 62	%	1.4 - 1.5
Water absorption, saturation			%	6.1

	Condition	Standard	Unit	Value
<b>Mechanical properties</b>				<b>dam / cond.*</b>
Tensile modulus	1 mm/min	ISO 527-1/-2	MPa	9500 / 6000
Stress at break		ISO 527-1/-2	MPa	165 / 100
Strain at break		ISO 527-1/-2	%	3 / 6.1
Flexural modulus, ISO 178	2 mm/min	ISO 178	MPa	8500 / 5500
Charpy impact strength, +23°C	+23°C	ISO 179/1eU	kJ/m <sup>2</sup>	70 / 85

\*: **conditioned according to ISO 1110**

	Condition	Standard	Unit	Value
<b>Thermal properties</b>				
Melting temperature, 10°C/min		ISO 11357-1	°C	221
Temp. of deflection under load, 0.45 MPa	0.45 MPa	ISO 75	°C	220
Temp. of deflection under load, 1.80 MPa	1.80 MPa	ISO 75	°C	200
Vicat softening temperature	50°C/h - 50N	ISO 306	°C	215

	Condition	Standard	Unit	Value
<b>Burning behaviour</b>				
Flammability, 0.75 mm	0.75 mm	UL 94		HB
Glow-wire flammability index, GWFI, 1.5 mm	1.5 mm	IEC 60695-2-12	°C	650
Burning rate, FMVSS, Thickness 1 mm		FMVSS 302		< 100mm/min

Condition	Standard	Unit	Value
-----------	----------	------	-------

## Electrical properties

Volume resistivity		IEC 62631-3-1	ohm.m	1.0E13
Surface resistivity		IEC 62631-3-1	ohm	1.0E13
Comparative tracking index	Solution A	IEC 60112	V	500.0
CTI performance level category		Sol A		PLC 1

## Processing conditions

Drying temperature/time	75-85°C / 2-4h (with dew point of dried air < -30 °C)
Suggested max moisture	0.2 %
Rear temperature	230 - 235 °C
Middle temperature	235 - 240 °C
Front temperature	240 - 250 °C
Recommended melt temperature	230 - 250 °C
Recommended mould temperature	60 - 90 °C

## Injection notes

The material is supplied in airtight bags, ready for use. In case that the virgin material has absorbed moisture, it must be dried with a dehumidified air drying equipment, dew point minimum -20°C. Recommended time 2-4h.

## Injection advice

For reinforced polyamides, Domo recommends the use of steel with a high content of carbon, and purified for polishing, to avoid or limit the abrasion. For example: X38CrMoV5-1 (EN Norm) - 1.2367 /1.2343 (DIN Norm) or X160CrMoV12 (EN Norm) - 1.2601 /1.2379 (DIN Norm). In the case of high requirements on surface quality a mould temperature of up to 120°C can be considered. The processing parameters like processing temperatures are a recommendation and can be adjusted in function of injection machine size, part geometry / design.