

TECHNICAL DATA SHEET

TECHNYL C 216 V20 BK 21NS

DOMAMID 6G20 202 BK

Polyamide 6, 20% glass fiber reinforced, for injection moulding, black

General

Polymer type	PA6
Certifications	RoHS
Feature	not heat stabilized
Processing technology	injection moulding

Product identification

ISO 1043 abbreviation	PA6-GF20
ISO 16396 designation	PA6,GF20,M,S14-070

Condition	Standard	Unit	Value
-----------	----------	------	-------

Physical properties

	Condition	Standard	Unit	Value
Density		ISO 1183	g/cm ³	1.27
Humidity absorption	T=23°C, 50% RH	ISO 62	%	1.1 - 1.2
Water absorption	24 hr, 23°C	ISO 62	%	>=6.0

	Condition	Standard	Unit	Value
Mechanical properties				dam / cond.*
Tensile modulus	1 mm/min	ISO 527-1/-2	MPa	7000 / -
Stress at break	5 mm/min	ISO 527-1/-2	MPa	145 / -
Strain at break	5 mm/min	ISO 527-1/-2	%	4 / -
Flexural modulus, ISO 178	2 mm/min	ISO 178	MPa	5500 / -
Charpy impact strength, +23°C	+23°C	ISO 179/1eU	kJ/m ²	60 / -
Charpy notched impact strength, +23°C	+23°C	ISO 179/1eA	kJ/m ²	9 / -

*: **conditioned according to ISO 1110**

	Condition	Standard	Unit	Value
Thermal properties				
Melting temperature, 10°C/min		ISO 11357-1	°C	221
Temp. of deflection under load, 0.45 MPa	0.45 MPa	ISO 75	°C	210
Temp. of deflection under load, 1.80 MPa	1.80 MPa	ISO 75	°C	195
Vicat softening temperature	50°C/h - 50N	ISO 306	°C	210

	Condition	Standard	Unit	Value
Burning behaviour				
Burning rate, FMVSS, Thickness 1 mm		FMVSS 302		< 100 mm/min

	Condition	Standard	Unit	Value
Electrical properties				
Volume resistivity		IEC 62631-3-1	ohm.m	1.0E13
Surface resistivity		IEC 62631-3-1	ohm	1.0E14

Processing conditions	
Drying temperature/time	75-85°C / 2-4h (with dew point of dried air < -30 °C)
Recommended melt temperature	250 - 290 °C

Processing conditions

Recommended mould temperature	80 - 100 °C
-------------------------------	-------------

Injection notes

The material is supplied in airtight bags, ready for use.,In case that the virgin material has absorbed moisture, it must be dried with a dehumidified air drying equipment, dew point minimum -20°C.,Recommended time 2-4h.

Injection advice

For reinforced polyamides, Domo recommends the use of steel with a high content of carbon, and purified for polishing, to avoid or limit the abrasion. For example: X38CrMoV5-1 (EN Norm) - 1.2367 /1.2343 (DIN Norm) or X160CrMoV12 (EN Norm) - 1.2601 /1.2379 (DIN Norm). In the case of high requirements on surface quality a mould temperature of up to 120°C can be considered.,The processing parameters like processing temperatures are a recommendation and can be adjusted in function of injection machine size, part geometry / design.