

TECHNICAL DATA SHEET

TECHNYL C 218 V15 BK

TECHNYL C 218 V15 BK is a polyamide 6, heat stabilized, reinforced with 15% of glass fiber, for injection moulding. The product offers an excellent combination between thermal and mechanical properties.

General

Polymer type	PA6
Certifications	RoHS EC 1907/2006 (REACH)
Feature	heat-aging stabilized
Applications	connectors
Colors available	black
Forms	pellets
Processing technology	injection moulding

Product identification

ISO 1043 abbreviation	PA6-GF15
ISO 16396 designation	PA6,GF15,M,S14-060

Condition	Standard	Unit	Value
-----------	----------	------	-------

Physical properties

	Condition	Standard	Unit	Value
Density		ISO 1183	g/cm ³	1.23
Water absorption	24 hr, 23°C	ISO 62	%	1.2
Molding shrinkage, parallel		ISO 294-4, 2577	%	0.3 - 0.5
Molding shrinkage, normal		ISO 294-4, 2577	%	0.9 - 1.1

	Condition	Standard	Unit	Value
Mechanical properties				dam / cond.*
Tensile modulus	1 mm/min	ISO 527-1/-2	MPa	6100 / 2900
Stress at break		ISO 527-1/-2	MPa	120 / 70
Strain at break		ISO 527-1/-2	%	3.5 / 6.5
Flexural modulus, ISO 178	2 mm/min	ISO 178	MPa	6000 / 2800
Flexural strength, ISO 178	2 mm/min	ISO 178	MPa	200 / -
Charpy impact strength, +23°C	+23°C	ISO 179/1eU	kJ/m ²	40 / 55
Charpy notched impact strength, +23°C	+23°C	ISO 179/1eA	kJ/m ²	5.5 / 16
Izod notched impact strength, +23°C	+23°C	ISO 180/1A	kJ/m ²	5 / 14

*: **conditioned according to ISO 1110**

	Condition	Standard	Unit	Value
Thermal properties				
Melting temperature, 10°C/min		ISO 11357-1	°C	222
Temp. of deflection under load, 1.80 MPa	1.80 MPa	ISO 75	°C	180

	Condition	Standard	Unit	Value
Burning behaviour				
Flammability, 0.75 mm	0.75 mm	UL 94		HB
Flammability, 1.5 mm	1.5 mm	UL 94		HB
Glow-wire flammability index, GWFI, 1.5 mm	1.5 mm	IEC 60695-2-12	°C	650
Burning rate, FMVSS, Thickness 1 mm		FMVSS 302		<100 mm/min

Condition	Standard	Unit	Value
-----------	----------	------	-------

Electrical properties

Volume resistivity		IEC 62631-3-1	ohm.m	1.0E13
Surface resistivity		IEC 62631-3-1	ohm	1.0E14
Comparative tracking index	Solution A	IEC 60112	V	550.0
CTI performance level category		Sol A		PLC 1

Processing conditions

Drying temperature/time	80 °C
Suggested max moisture	0.2 %
Rear temperature	230 - 235 °C
Middle temperature	235 - 240 °C
Front temperature	240 - 250 °C
Recommended mould temperature	60 - 90 °C

Injection notes

The material is supplied in airtight bags, ready for use.,In case that the virgin material has absorbed moisture, it must be dried with a dehumidified air drying equipment, dew point minimum -20°C.,Recommended time 2-4h.

Injection advice

For reinforced polyamides, Domo recommends the use of steel with a high content of carbon, and purified for polishing, to avoid or limit the abrasion. For example: X38CrMoV5-1 (EN Norm) - 1.2367 /1.2343 (DIN Norm) or X160CrMoV12 (EN Norm) - 1.2601 /1.2379 (DIN Norm). In the case of high requirements on surface quality a mould temperature of up to 120°C can be considered.,The processing parameters like processing temperatures are a recommendation and can be adjusted in function of injection machine size, part geometry / design.