

TECHNICAL DATA SHEET

TECHNYL C 218 V15 NC

DOMAMID 6G15H2 NC

Polyamide 6, 15% glass fiber reinforced, heat-aging stabilized, for injection moulding, natural color

General

Certifications	RoHS
Polymer type	PA6
Feature	heat-aging stabilized
Processing technology	injection moulding

Product identification

ISO 1043 abbreviation	PA6-GF15
ISO 16396 designation	PA6,GF15,MH,S14-060

Condition	Standard	Unit	Value
-----------	----------	------	-------

Physical properties

Density		ISO 1183	g/cm ³	1.23
Humidity absorption	T=23°C, 50% RH	ISO 62	%	2.4 - 2.8
Water absorption	24 hr, 23°C	ISO 62	%	1.5 - 1.6
Water absorption, saturation			%	7.5
Molding shrinkage, parallel		ISO 294-4, 2577	%	0.4 - 0.6
Molding shrinkage, normal		ISO 294-4, 2577	%	0.85 - 1.05
Melt volume-flow rate, MVR, 5.0 kg	275°C, 5kg	ISO 1133	cm ³ /10 min	80.0
Viscosity number	96% H2SO4	ISO 307	cm ³ /g	140.0

	Condition	Standard	Unit	Value
Mechanical properties				dam / cond.*
Tensile modulus	1 mm/min	ISO 527-1/-2	MPa	5700 / -
Stress at break	5 mm/min	ISO 527-1/-2	MPa	130 / -
Strain at break	5 mm/min	ISO 527-1/-2	%	3.5 / -
Flexural modulus, ISO 178	2 mm/min	ISO 178	MPa	4300 / -
Charpy impact strength, +23°C	+23°C	ISO 179/1eU	kJ/m ²	45 / -
Charpy notched impact strength, +23°C	+23°C	ISO 179/1eA	kJ/m ²	6 / -

*: **conditioned according to ISO 1110**

	Condition	Standard	Unit	Value
Thermal properties				
Melting temperature, 10°C/min		ISO 11357-1	°C	221
Temp. of deflection under load, 0.45 MPa	0.45 MPa	ISO 75	°C	215
Temp. of deflection under load, 1.80 MPa	1.80 MPa	ISO 75	°C	190
Vicat softening temperature	50°C/h - 50N	ISO 306	°C	210

	Condition	Standard	Unit	Value
Burning behaviour				
Burning rate, FMVSS, Thickness 1 mm		FMVSS 302		< 100 mm/min

	Condition	Standard	Unit	Value
Electrical properties				
Volume resistivity		IEC 62631-3-1	ohm.m	1.0E13
Surface resistivity		IEC 62631-3-1	ohm	1.0E14

Processing conditions

Drying temperature/time	75-85°C / 2-4h (with dew point of dried air < -30 °C)
Recommended melt temperature	250 - 290 °C

Processing conditions

Recommended mould temperature	80 - 100 °C
-------------------------------	-------------

Injection notes

The material is supplied in airtight bags, ready for use.,In case that the virgin material has absorbed moisture, it must be dried with a dehumidified air drying equipment, dew point minimum -20°C.,Recommended time 2-4h.

Injection advice

For reinforced polyamides, Domo recommends the use of steel with a high content of carbon, and purified for polishing, to avoid or limit the abrasion. For example: X38CrMoV5-1 (EN Norm) - 1.2367 / 1.2343 (DIN Norm) or X160CrMoV12 (EN Norm) - 1.2601 / 1.2379 (DIN Norm). In the case of high requirements on surface quality a mould temperature of up to 120°C can be considered.,The processing parameters like processing temperatures are a recommendation and can be adjusted in function of injection machine size, part geometry / design.