

TECHNICAL DATA SHEET

TECHNYL C 216L1 V30 GY 7391XB

DOMAMID 6G30UV1 GY77391XB

General

Certifications	RoHS	EC 1907/2006 (REACH)
Polymer type	PA6	
Colors available	black grey	natural
Forms	pellets	
Processing technology	injection moulding	

Product identification

ISO 1043 abbreviation	PA6
ISO 16396 designation	PA6,M1L1,S14-030

Condition	Standard	Unit	Value
-----------	----------	------	-------

Physical properties

	Condition	Standard	Unit	Value
Density		ISO 1183	g/cm ³	1.14
Molding shrinkage, parallel		ISO 294-4, 2577	%	0.85 - 0.95
Molding shrinkage, normal		ISO 294-4, 2577	%	0.95 - 1.05
Melt volume-flow rate, MVR, 5.0 kg	275°C, 5kg	ISO 1133	cm ³ /10 min	165.0
Viscosity number	96% H2SO4	ISO 307	cm ³ /g	145.0

	Condition	Standard	Unit	Value
Mechanical properties				dam / cond.*
Tensile modulus	1 mm/min	ISO 527-1/-2	MPa	3200 / 1000
Yield stress		ISO 527-1/-2	MPa	75 / 35
Flexural modulus, ISO 178	2 mm/min	ISO 178	MPa	2800 / 900
Flexural strength, ISO 178	2 mm/min	ISO 178	MPa	105 / 35
Charpy impact strength, +23°C	+23°C	ISO 179/1eU	kJ/m ²	NB
Charpy notched impact strength, +23°C	+23°C	ISO 179/1eA	kJ/m ²	8 / 25
Izod notched impact strength, +23°C	+23°C	ISO 180/1A	kJ/m ²	8 / 25
Rockwell hardness		ISO 2039/2	ScaleR	120 / -

*: **conditioned according to ISO 1110**

	Condition	Standard	Unit	Value
Thermal properties				
Melting temperature, 10°C/min		ISO 11357-1	°C	221
Temp. of deflection under load, 0.45 MPa	0.45 MPa	ISO 75	°C	175
Temp. of deflection under load, 1.80 MPa	1.80 MPa	ISO 75	°C	65
Vicat softening temperature	50°C/h - 50N	ISO 306	°C	200

	Condition	Standard	Unit	Value
Burning behaviour				
Flammability		UL 94		V2
Glow-wire flammability index, GWFI	1-3 mm	IEC 60695-2-12	°C	750
Burning rate, FMVSS, Thickness 1 mm		FMVSS 302		<100

Condition	Standard	Unit	Value
-----------	----------	------	-------

Electrical properties

Volume resistivity		IEC 62631-3-1	ohm.m	1.0E16
Surface resistivity		IEC 62631-3-1	ohm	1.0E14
Comparative tracking index	Solution A	IEC 60112	V	600.0
CTI performance level category		Sol A		PLC 0

Processing conditions

Drying temperature/time	75-85°C / 2-4h (with dew point of dried air < -30 °C)
Rear temperature	230 °C
Middle temperature	235 °C
Front temperature	235 °C
Recommended melt temperature	230 °C
Recommended mould temperature	60 °C