

TECHNICAL DATA SHEET

TECHNYL C 216L1

DOMAMID 6UV1

Polyamide 6, UV-stabilized, for injection moulding. For Asian availability only

General

Polymer type	PA6		
Certifications	RoHS	EC 1907/2006 (REACH)	
Feature	UV stabilized	not heat stabilized	
Colors available	natural		
Forms	pellets		
Processing technology	injection moulding		

Product identification

ISO 1043 abbreviation	PA6		
ISO 16396 designation	PA6,ML1,S14-030		

Condition	Standard	Unit	Value
-----------	----------	------	-------

Physical properties

Condition	Standard	Unit	Value	
Density	ISO 1183	g/cm ³	1.14	
Humidity absorption	T=23°C, 50% RH	ISO 62	%	3.3 - 3.4
Water absorption	24 hr, 23°C	ISO 62	%	1.9 - 2.0
Water absorption, saturation			%	9.1
Molding shrinkage, parallel	ISO 294-4, 2577	%		0.9 - 1.1
Molding shrinkage, normal	ISO 294-4, 2577	%		1.0 - 1.2
Melt volume-flow rate, MVR, 5.0 kg	275°C, 5kg	ISO 1133	cm ³ /10 min	165.0
Viscosity number	96% H2SO4	ISO 307	cm ³ /g	145.0

	Condition	Standard	Unit	Value
Mechanical properties				dam / cond.*
Tensile modulus	1 mm/min	ISO 527-1/-2	MPa	3200 / 1000
Strain at break	50 mm/min	ISO 527-1/-2	%	40 / 50
Yield stress	50 mm/min	ISO 527-1/-2	MPa	80 / 40
Flexural modulus, ISO 178	2 mm/min	ISO 178	MPa	2800 / 900
Flexural strength, ISO 178	2 mm/min	ISO 178	MPa	105 / 35
Rockwell hardness		ISO 2039/2	ScaleR	120 / -

*: **conditioned according to ISO 1110**

	Condition	Standard	Unit	Value
Thermal properties				
Temp. of deflection under load, 0.45 MPa	0.45 MPa	ISO 75	°C	175
Temp. of deflection under load, 1.80 MPa	1.80 MPa	ISO 75	°C	65
Vicat softening temperature	50Å°C/h - 50N	ISO 306	°C	200

	Condition	Standard	Unit	Value
Burning behaviour				
Flammability, 0.75 mm	0.75 mm	UL 94		V2
Glow-wire flammability index, GWFI	1-3 mm	IEC 60695-2-12	°C	850
Burning rate, FMVSS, Thickness 1 mm		FMVSS 302		< 100 mm/min

	Condition	Standard	Unit	Value
Electrical properties				
Volume resistivity		IEC 62631-3-1	ohm.m	1.0E16
Surface resistivity		IEC 62631-3-1	ohm	1.0E14
Comparative tracking index	Solution A	IEC 60112	V	600.0
CTI performance level category		Sol A		PLC 0

Processing conditions

Drying temperature/time	75-85Å°C / 2-4h (with dew point of dried air < -30 Å°C)
Rear temperature	235 Å°C
Middle temperature	240 Å°C
Front temperature	245 Å°C
Recommended melt temperature	245 Å°C
Recommended mould temperature	90 Å°C

Injection notes

The material is supplied in airtight bags, ready for use.,In case that the virgin material has absorbed moisture, it must be dried with a dehumidified air drying equipment, dew point minimum -20Å°C.,Recommended time 2-4h.

Injection advice

For reinforced polyamides, Domo recommends the use of steel with a high content of carbon, and purified for polishing, to avoid or limit the abrasion. For example: X38CrMoV5-1 (EN Norm) - 1.2367 /1.2343 (DIN Norm) or X160CrMoV12 (EN Norm) - 1.2601 /1.2379 (DIN Norm). In the case of high requirements on surface quality a mould temperature of up to 120Å°C can be considered.,The processing parameters like processing temperatures are a recommendation and can be adjusted in function of injection machine size, part geometry / design.