

TECHNICAL DATA SHEET

TECHNYL C 216L1 V15 BK 9280

DOMAMID 6G15UV1

Polyamide 6, 15% glass fiber reinforced, UV-stabilized, for injection moulding

General

Certifications	RoHS
Polymer type	PA6
Feature	UV stabilized
Processing technology	injection moulding

Product identification

ISO 1043 abbreviation	PA6-GF15
ISO 16396 designation	PA6,GF15,M1L1,S14-060

Condition	Standard	Unit	Value
-----------	----------	------	-------

Physical properties

Density		ISO 1183	g/cm ³	1.23
Humidity absorption	T=23°C, 50% RH	ISO 62	%	2.5
Water absorption	24 hr, 23°C	ISO 62	%	8.0
Molding shrinkage, parallel		ISO 294-4, 2577	%	0.4 - 0.6
Molding shrinkage, normal		ISO 294-4, 2577	%	0.8 - 1.0
Melt volume-flow rate, MVR, 5.0 kg	275°C, 5kg	ISO 1133	cm ³ /10 min	50.0
Viscosity number	96% H2SO4	ISO 307	cm ³ /g	145.0

	Condition	Standard	Unit	Value
Mechanical properties				dam / cond.*
Tensile modulus	1 mm/min	ISO 527-1/-2	MPa	6100 / -
Stress at break	5 mm/min	ISO 527-1/-2	MPa	130 / -
Strain at break	5 mm/min	ISO 527-1/-2	%	3.5 / -
Flexural modulus, ISO 178	2 mm/min	ISO 178	MPa	5200 / -
Flexural strength, ISO 178	2 mm/min	ISO 178	MPa	200 / -
Charpy impact strength, +23°C	+23°C	ISO 179/1eU	kJ/m ²	45 / -
Charpy notched impact strength, +23°C	+23°C	ISO 179/1eA	kJ/m ²	7 / -
Izod impact strength, +23°C	+23°C	ISO 180/1U	kJ/m ²	40 / -
Izod notched impact strength, +23°C	+23°C	ISO 180/1A	kJ/m ²	7 / -
Rockwell hardness		ISO 2039/2	ScaleR	120 / -

*: **conditioned according to ISO 1110**

	Condition	Standard	Unit	Value
Thermal properties				
Melting temperature, 10°C/min		ISO 11357-1	°C	221
Temp. of deflection under load, 0.45 MPa	0.45 MPa	ISO 75	°C	215
Temp. of deflection under load, 1.80 MPa	1.80 MPa	ISO 75	°C	190
Vicat softening temperature	50°C/h - 50N	ISO 306	°C	210

	Condition	Standard	Unit	Value
Burning behaviour				
Flammability, 0.75 mm	0.75 mm	UL 94		HB
Burning rate, FMVSS, Thickness 1 mm		FMVSS 302		< 100 mm/min

Condition	Standard	Unit	Value
-----------	----------	------	-------

Electrical properties

Volume resistivity		IEC 62631-3-1	ohm.m	1.0E13
Surface resistivity		IEC 62631-3-1	ohm	1.0E13
Comparative tracking index	Solution A	IEC 60112	V	500.0
CTI performance level category		Sol A		PLC 1

Processing conditions

Drying temperature/time	75-85°C / 2-4h (with dew point of dried air < -30 °C)
Recommended melt temperature	240 - 260 °C
Recommended mould temperature	80 - 90 °C