

TECHNICAL DATA SHEET

TECHNYL C 218 V30 NC

DOMAMID 6G30H2 NC / TECHNYL C 218 V30 NATURAL

TECHNYL C 218 V30 NC is a polyamide 6, reinforced with 30% of glass fiber, heat stabilized, for injection moulding. The product offers an excellent combination between thermal and mechanical properties.

General

Certifications	RoHS	EC 1907/2006 (REACH)
Polymer type	PA6	
Feature	heat-aging stabilized	
Applications	consumer applications industrial applications	general purpose
Colors available	natural	
Forms	pellets	
Processing technology	injection moulding	

Product identification

ISO 1043 abbreviation	PA6-GF30
ISO 16396 designation	PA6,GF30,MH,S14-090

Condition	Standard	Unit	Value
-----------	----------	------	-------

Physical properties

Condition	Standard	Unit	Value	
Density	ISO 1183	g/cm ³	1.36	
Humidity absorption	T=23°C, 50% RH	ISO 62	%	2.2 - 2.4
Water absorption	24 hr, 23°C	ISO 62	%	1.4 - 1.5
Water absorption, saturation			%	6.1
Molding shrinkage, parallel	ISO 294-4, 2577	%		0.25 - 0.45
Molding shrinkage, normal	ISO 294-4, 2577	%		0.85 - 1.05
Viscosity number	96% H2SO4	ISO 307	cm ³ /g	145.0

	Condition	Standard	Unit	Value
Mechanical properties				dam / cond.*
Tensile modulus	1 mm/min	ISO 527-1/-2	MPa	9500 / 6000
Stress at break	5 mm/min	ISO 527-1/-2	MPa	180 / 105
Strain at break	5 mm/min	ISO 527-1/-2	%	3.6 / 8
Flexural modulus, ISO 178	2 mm/min	ISO 178	MPa	7400 / 4900
Flexural strength, ISO 178	2 mm/min	ISO 178	MPa	270 / 170
Charpy impact strength, +23°C	+23°C	ISO 179/1eU	kJ/m ²	95 / 110
Charpy impact strength, -30°C	-30°C	ISO 179/1eU	kJ/m ²	75 / 80
Charpy notched impact strength, +23°C	+23°C	ISO 179/1eA	kJ/m ²	13 / 25
Charpy notched impact strength, -30°C	-30°C	ISO 179/1eA	kJ/m ²	10 / 11

*: **conditioned according to ISO 1110**

	Condition	Standard	Unit	Value
Thermal properties				
Melting temperature, 10°C/min		ISO 11357-1	°C	221
Temp. of deflection under load, 0.45 MPa	0.45 MPa	ISO 75	°C	220
Temp. of deflection under load, 1.80 MPa	1.80 MPa	ISO 75	°C	210
Vicat softening temperature	50°C/h - 50N	ISO 306	°C	214

	Condition	Standard	Unit	Value
Burning behaviour				
UL Yellow Card availability 1	<u>Click here to have access to the UL Yellow Card availability 1 -> E44716</u>			
Flammability, 0.75 mm	0.75 mm	UL 94		HB
Flammability, 1.5 mm	1.5 mm	UL 94		HB
Flammability, 3.0 mm	3.0 mm	UL 94		HB
Burning rate, FMVSS, Thickness 1 mm		FMVSS 302		< 100 mm/min

Condition	Standard	Unit	Value
-----------	----------	------	-------

Electrical properties

Volume resistivity		IEC 62631-3-1	ohm.m	1.0E13
Surface resistivity		IEC 62631-3-1	ohm	1.0E14

Processing conditions

Drying temperature/time	75-85°C / 2-4h (with dew point of dried air < -30 °C)
Rear temperature	230 - 235 °C
Middle temperature	235 - 240 °C
Front temperature	240 - 250 °C
Recommended melt temperature	230 - 250 °C
Recommended mould temperature	60 - 90 °C

Injection notes

The material is supplied in airtight bags, ready for use. In case that the virgin material has absorbed moisture, it must be dried with a dehumidified air drying equipment, dew point minimum -20°C. Recommended time 2-4h.

Injection advice

For reinforced polyamides, Domo recommends the use of steel with a high content of carbon, and purified for polishing, to avoid or limit the abrasion. For example: X38CrMoV5-1 (EN Norm) - 1.2367 /1.2343 (DIN Norm) or X160CrMoV12 (EN Norm) - 1.2601 /1.2379 (DIN Norm). In the case of high requirements on surface quality a mould temperature of up to 120°C can be considered. The processing parameters like processing temperatures are a recommendation and can be adjusted in function of injection machine size, part geometry / design.