

TECHNICAL DATA SHEET

TECHNYL C 218 V35 BK

TECHNY C 218 V35 BK is a polyamide 6, reinforced with 35% of glass fiber, heat stabilized, for injection moulding. The product offers an excellent combination between thermal and mechanical properties.

General

Polymer type	PA6		
Certifications	RoHS	EC 1907/2006 (REACH)	
Feature	heat-aging stabilized		
Applications	automotive applications	consumer applications	
Colors available	black	natural	
Forms	pellets		
Processing technology	injection moulding		

Product identification

ISO 1043 abbreviation	PA6-GF35
ISO 16396 designation	PA6,GF35,MH,S14-110

Condition	Standard	Unit	Value
-----------	----------	------	-------

Physical properties

Condition	Standard	Unit	Value
Density	ISO 1183	g/cm ³	1.41
Humidity absorption	T=23°C, 50% RH	%	1.8 - 2.2
Water absorption	24 hr, 23°C	%	1.4 - 1.5
Water absorption, saturation		%	5.9
Molding shrinkage, parallel	ISO 294-4, 2577	%	0.25
Molding shrinkage, normal	ISO 294-4, 2577	%	0.7

	Condition	Standard	Unit	Value
Mechanical properties				dam / cond.*
Tensile modulus	1 mm/min	ISO 527-1/-2	MPa	11000 / 6500
Stress at break		ISO 527-1/-2	MPa	175 / 110
Strain at break		ISO 527-1/-2	%	3.2 / 7
Flexural modulus, ISO 178	2 mm/min	ISO 178	MPa	9600 / 6000
Flexural strength, ISO 178	2 mm/min	ISO 178	MPa	280 / 185
Charpy impact strength, +23°C	+23°C	ISO 179/1eU	kJ/m ²	83 / 94
Charpy notched impact strength, +23°C	+23°C	ISO 179/1eA	kJ/m ²	17 / 19
Izod notched impact strength, +23°C	+23°C	ISO 180/1A	kJ/m ²	15 / 28

*: **conditioned according to ISO 1110**

	Condition	Standard	Unit	Value
Thermal properties				
Melting temperature, 10°C/min		ISO 11357-1	°C	222
Temp. of deflection under load, 0.45 MPa	0.45 MPa	ISO 75	°C	220
Temp. of deflection under load, 1.80 MPa	1.80 MPa	ISO 75	°C	210

	Condition	Standard	Unit	Value
Burning behaviour				
Glow-wire flammability index, GWFI, 1.5 mm	1.5 mm	IEC 60695-2-12	°C	650
Glow-wire flammability index, GWFI, 3.0 mm			°C	650
Burning rate, FMVSS, Thickness 1 mm		FMVSS 302		<100 mm/min

Condition	Standard	Unit	Value
-----------	----------	------	-------

Electrical properties

Volume resistivity		IEC 62631-3-1	ohm.m	1.0E13
Surface resistivity		IEC 62631-3-1	ohm	1.0E14
Comparative tracking index	Solution A	IEC 60112	V	400.0
CTI performance level category		Sol A		PLC 1

Processing conditions

Drying temperature/time	80°C / 2-4h
Suggested max moisture	0.2 %
Rear temperature	240 - 250 °C
Middle temperature	250 - 270 °C
Front temperature	260 - 290 °C
Recommended mould temperature	60 - 90 °C

Injection notes

The material is supplied in airtight bags, ready for use.,In case that the virgin material has absorbed moisture, it must be dried with a dehumidified air drying equipment, dew point minimum -20°C.,Recommended time 2-4h.

Injection advice

For reinforced polyamides, Domo recommends the use of steel with a high content of carbon, and purified for polishing, to avoid or limit the abrasion. For example: X38CrMoV5-1 (EN Norm) - 1.2367 /1.2343 (DIN Norm) or X160CrMoV12 (EN Norm) - 1.2601 /1.2379 (DIN Norm). In the case of high requirements on surface quality a mould temperature of up to 120°C can be considered.,The processing parameters like processing temperatures are a recommendation and can be adjusted in function of injection machine size, part geometry / design.