

TECHNICAL DATA SHEET

TECHNYL C 246 V30 NC

TECHNYL C 246 V30 NC is a polyamide 6, reinforced with 30 % of glass fibre, impact modified, for injection moulding. This grade offers high impact strength and good mechanical properties.

General

Certifications	RoHS EC 1907/2006 (REACH)	UL listed product
Polymer type	PA6	
Feature	good surface finish	high impact resistant
Applications	consumer applications power tool / garden equipment	outdoor applications sport
Colors available	natural	
Forms	pellets	
Processing technology	injection moulding	

Product identification

ISO 1043 abbreviation	PA6-GF30
-----------------------	----------

Condition	Standard	Unit	Value
-----------	----------	------	-------

Physical properties

	Condition	Standard	Unit	Value
Density		ISO 1183	g/cm ³	1.32
Water absorption	24 hr, 23°C	ISO 62	%	0.95
Molding shrinkage, parallel		ISO 294-4, 2577	%	0.06
Molding shrinkage, normal		ISO 294-4, 2577	%	0.85

	Condition	Standard	Unit	Value
Mechanical properties				dam / cond.*
Tensile modulus	1 mm/min	ISO 527-1/-2	MPa	8200 / 5400
Stress at break		ISO 527-1/-2	MPa	140 / 90
Strain at break		ISO 527-1/-2	%	4 / 6
Flexural modulus, ISO 178	2 mm/min	ISO 178	MPa	8000 / 5200
Charpy impact strength, +23°C	+23°C	ISO 179/1eU	kJ/m ²	86 / 100
Charpy impact strength, -30°C	-30°C	ISO 179/1eU	kJ/m ²	85 / -
Charpy notched impact strength, +23°C	+23°C	ISO 179/1eA	kJ/m ²	18 / 30
Charpy notched impact strength, -30°C	-30°C	ISO 179/1eA	kJ/m ²	11 / -
Izod notched impact strength, +23°C	+23°C	ISO 180/1A	kJ/m ²	17 / 29

*: **conditioned according to ISO 1110**



	Condition	Standard	Unit	Value
Thermal properties				
Melting temperature, 10°C/min		ISO 11357-1	°C	222
Temp. of deflection under load, 1.80 MPa	1.80 MPa	ISO 75	°C	200

	Condition	Standard	Unit	Value
Burning behaviour				
UL Yellow Card availability 1		Click here to have access to the UL Yellow Card availability 1 -> QMFZ2.E44716		
Flammability, 1.5 mm	1.5 mm	UL 94		HB

	Condition	Standard	Unit	Value
Electrical properties				
Volume resistivity		IEC 62631-3-1	ohm.m	1.0E13
Surface resistivity		IEC 62631-3-1	ohm	1.0E14

Processing conditions

Drying temperature/time	80 °C
Suggested max moisture	0.2 %
Rear temperature	230 - 235 °C
Middle temperature	235 - 240 °C
Front temperature	240 - 250 °C
Recommended mould temperature	60 - 90 °C



Injection notes

The material is supplied in airtight bags, ready for use. In case that the virgin material has absorbed moisture, it must be dried with a dehumidified air drying equipment, dew point minimum -20°C. Recommended time 2-4h.

Injection advice

For reinforced polyamides, Domo recommends the use of steel with a high content of carbon, and purified for polishing, to avoid or limit the abrasion. For example: X38CrMoV5-1 (EN Norm) - 1.2367 /1.2343 (DIN Norm) or X160CrMoV12 (EN Norm) - 1.2601 /1.2379 (DIN Norm). In the case of high requirements on surface quality a mould temperature of up to 120°C can be considered. The processing parameters like processing temperatures are a recommendation and can be adjusted in function of injection machine size, part geometry / design.