

TECHNICAL DATA SHEET

## TECHNYL C 236 V35 BK Z

TECHNYL C 236 V35 BK Z is a polyamide 6 reinforced with 35% of glass fiber, with improved impact resistance, for injection moulding. This grade offer a high impact strength and good mechanical properties.

### General

Polymer type	PA6		
Certifications	RoHS EC 1907/2006 (REACH)	UL listed product	
Feature	impact resistant(obs)		
Applications	consumer applications wire / cable applications	industrial applications	
Colors available	black		
Forms	pellets		
Processing technology	injection moulding		

### Product identification

ISO 1043 abbreviation	PA6-GF35
-----------------------	----------

Condition	Standard	Unit	Value
-----------	----------	------	-------

### Physical properties

	Condition	Standard	Unit	Value
Density		ISO 1183	g/cm <sup>3</sup>	1.41
Water absorption	24 hr, 23°C	ISO 62	%	0.9

	Condition	Standard	Unit	Value
<b>Mechanical properties</b>				<b>dam / cond.*</b>
Tensile modulus	1 mm/min	ISO 527-1/-2	MPa	9700 / -
Stress at break		ISO 527-1/-2	MPa	160 / -
Strain at break		ISO 527-1/-2	%	3.6 / -
Flexural modulus, ISO 178	2 mm/min	ISO 178	MPa	8600 / -
Flexural strength, ISO 178	2 mm/min	ISO 178	MPa	243 / -
Charpy impact strength, +23°C	+23°C	ISO 179/1eU	kJ/m <sup>2</sup>	86 / -
Charpy notched impact strength, +23°C	+23°C	ISO 179/1eA	kJ/m <sup>2</sup>	15 / -

\*: **conditioned according to ISO 1110**

	Condition	Standard	Unit	Value
<b>Thermal properties</b>				
Melting temperature, 10°C/min		ISO 11357-1	°C	222

	Condition	Standard	Unit	Value
<b>Burning behaviour</b>				
UL Yellow Card availability 1	<a href="#"><b>Click here to have access to the UL Yellow Card availability 1 -&gt; QMFZ2.E44716</b></a>			
Flammability, 0.75 mm	0.75 mm	UL 94		HB

<b>Processing conditions</b>	
Drying temperature/time	80 °C
Suggested max moisture	0.2 %
Rear temperature	230 - 235 °C
Middle temperature	235 - 240 °C
Front temperature	240 - 250 °C
Recommended mould temperature	60 - 90 °C

# TECHNYL®

**DOMO**  
caring is our formula

TECHNICAL DATA SHEET

TECHNYL C 236 V35 BK Z

## Injection notes

The material is supplied in airtight bags, ready for use. In case that the virgin material has absorbed moisture, it must be dried with a dehumidified air drying equipment, dew point minimum -20°C. Recommended time 2-4h.

## Injection advice

For reinforced polyamides, Domo recommends the use of steel with a high content of carbon, and purified for polishing, to avoid or limit the abrasion. For example: X38CrMoV5-1 (EN Norm) - 1.2367 / 1.2343 (DIN Norm) or X160CrMoV12 (EN Norm) - 1.2601 / 1.2379 (DIN Norm). In the case of high requirements on surface quality a mould temperature of up to 120°C can be considered.