

TECHNICAL DATA SHEET

TECHNYL C 236SI V30 NC

TECHNYL C 236SI V30 NC is a polyamide 6 reinforced with 30% of glass fiber, with improved impact resistance, for injection moulding. This grade offers high impact strength and good mechanical properties.

General

Certifications	RoHS	EC 1907/2006 (REACH)
Polymer type	PA6	
Feature	high impact resistant	
Applications	consumer applications outdoor applications	industrial applications sport
Colors available	natural	
Forms	pellets	
Processing technology	injection moulding	

Product identification

ISO 1043 abbreviation	PA6-GF30
-----------------------	----------

Condition	Standard	Unit	Value
-----------	----------	------	-------

Physical properties

	Condition	Standard	Unit	Value
Density		ISO 1183	g/cm ³	1.34
Water absorption	24 hr, 23°C	ISO 62	%	0.93

	Condition	Standard	Unit	Value
Mechanical properties				dam / cond.*
Tensile modulus	1 mm/min	ISO 527-1/-2	MPa	9500 / 5200
Stress at break		ISO 527-1/-2	MPa	150 / 95
Strain at break		ISO 527-1/-2	%	4 / -
Flexural modulus, ISO 178	2 mm/min	ISO 178	MPa	7600 / 4000
Flexural strength, ISO 178	2 mm/min	ISO 178	MPa	227 / -
Charpy impact strength, +23°C	+23°C	ISO 179/1eU	kJ/m ²	92 / 100
Charpy impact strength, -30°C	-30°C	ISO 179/1eU	kJ/m ²	98 / 98
Charpy notched impact strength, +23°C	+23°C	ISO 179/1eA	kJ/m ²	18 / 32
Charpy notched impact strength, -30°C	-30°C	ISO 179/1eA	kJ/m ²	13 / -

*: **conditioned according to ISO 1110**

	Condition	Standard	Unit	Value
Thermal properties				
Melting temperature, 10°C/min		ISO 11357-1	°C	222
Temp. of deflection under load, 1.80 MPa	1.80 MPa	ISO 75	°C	205

Processing conditions

Drying temperature/time	80 °C
Suggested max moisture	0.08 %
Rear temperature	250 - 270 °C
Middle temperature	260 - 280 °C
Front temperature	260 - 290 °C
Recommended mould temperature	70 - 90 °C

Injection notes

The material is supplied in airtight bags, ready for use.,In case that the virgin material has absorbed moisture, it must be dried with a dehumidified air drying equipment, dew point minimum -20°C.,Recommended time 2-4h.

TECHNYL®

DOMO
caring is our formula

TECHNICAL DATA SHEET

TECHNYL C 236SI V30 NC

Injection advice

For reinforced polyamides, Domo recommends the use of steel with a high content of carbon, and purified for polishing, to avoid or limit the abrasion. For example: X38CrMoV5-1 (EN Norm) - 1.2367 /1.2343 (DIN Norm) or X160CrMoV12 (EN Norm) - 1.2601 /1.2379 (DIN Norm). In the case of high requirements on surface quality a mould temperature of up to 120°C can be considered.,The processing parameters like processing temperatures are a recommendation and can be adjusted in function of injection machine size, part geometry / design.