

TECHNICAL DATA SHEET

TECHNYL C 249L1 V30 RD 3202

DOMAMID 6G30I1H1UV1 RD33202

Polyamide 6, 30% glass fiber reinforced, heat-aging stabilized, UV-stabilized, impact modified, for injection moulding

General

Certifications	RoHS		
Polymer type	PA6		
Feature	heat-aging stabilized UV stabilized	impact modified	
Processing technology	injection moulding		

Product identification

ISO 1043 abbreviation	PA6-I-GF30
ISO 16396 designation	PA6-I,GF30,M1HL1,S14-090

Condition	Standard	Unit	Value
-----------	----------	------	-------

Physical properties

Condition	Standard	Unit	Value
Density	ISO 1183	g/cm ³	1.32
Molding shrinkage, parallel	ISO 294-4, 2577	%	0.4 - 0.6
Molding shrinkage, normal	ISO 294-4, 2577	%	0.9 - 1.1

	Condition	Standard	Unit	Value
Mechanical properties				dam / cond.*
Tensile modulus	1 mm/min	ISO 527-1/-2	MPa	7300 / 4650
Stress at break	5 mm/min	ISO 527-1/-2	MPa	120 / 85
Strain at break	5 mm/min	ISO 527-1/-2	%	3.8 / 5.9
Flexural modulus, ISO 178	2 mm/min	ISO 178	MPa	6500 / 4000
Flexural strength, ISO 178	2 mm/min	ISO 178	MPa	195 / 115
Charpy impact strength, +23°C	+23°C	ISO 179/1eU	kJ/m ²	85 / 100
Charpy notched impact strength, +23°C	+23°C	ISO 179/1eA	kJ/m ²	11 / 19
Izod impact strength, +23°C	+23°C	ISO 180/1U	kJ/m ²	75 / 90
Izod notched impact strength, +23°C	+23°C	ISO 180/1A	kJ/m ²	11 / 19

*: **conditioned according to ISO 1110**

	Condition	Standard	Unit	Value
Thermal properties				
Melting temperature, 10°C/min		ISO 11357-1	°C	221
Temp. of deflection under load, 0.45 MPa	0.45 MPa	ISO 75	°C	210
Temp. of deflection under load, 1.80 MPa	1.80 MPa	ISO 75	°C	195
Vicat softening temperature	50°C/h - 50N	ISO 306	°C	205

	Condition	Standard	Unit	Value
Burning behaviour				
Flammability, 0.75 mm	0.75 mm	UL 94		HB
Burning rate, FMVSS, Thickness 1 mm		FMVSS 302		< 100 mm/min

Condition	Standard	Unit	Value
-----------	----------	------	-------

Electrical properties

Volume resistivity		IEC 62631-3-1	ohm.m	1.0E13
Surface resistivity		IEC 62631-3-1	ohm	1.0E13

Processing conditions

Drying temperature/time	75-85°C / 2-4h (with dew point of dried air < -30 °C)
Recommended melt temperature	240 - 270 °C
Recommended mould temperature	90 - 120 °C