

TECHNICAL DATA SHEET

TECHNYL PROTECT C 30H1 V30 NC/F
TECHNYL C 30H1 V30 NATURAL/F



TECHNYL PROTECT C 30H1 V30 NC/F is a flame retardant polyamide PA6, reinforced with 30% of glass fibre, for injection moulding. This grade has good mechanical properties, flame retardant rating UL94 V0 and glow-wire at 960°C.

General

Polymer type	PA6		
Certifications	RoHS	EC 1907/2006 (REACH)	
Feature	flame retarded good stiffness	UL 94 V0	
Applications	electrical/electronic applications		
Colors available	natural		
Forms	pellets		
Processing technology	injection moulding		

Product identification

ISO 1043 abbreviation	PA6,GF30FR(17)
ISO 16396 designation	PA6,GF30FR(17),M,S14-120

Condition	Standard	Unit	Value
-----------	----------	------	-------

Physical properties

Density		ISO 1183	g/cm ³	1.62
Humidity absorption	T=23°C, 50% RH (equivalent ISO 1110)	ISO 62	%	2.1 - 2.2
Water absorption	24 hr, 23°C, immersion in water, thickness 2mm	ISO 62	%	1.3 - 1.4
Molding shrinkage, parallel		ISO 294-4, 2577	%	0.1 - 0.2
Molding shrinkage, normal		ISO 294-4, 2577	%	0.6 - 0.7

	Condition	Standard	Unit	Value
Mechanical properties				dam / cond.*
Tensile modulus	1 mm/min	ISO 527-1/-2	MPa	12000 / 9100
Stress at break		ISO 527-1/-2	MPa	125 / 90
Strain at break		ISO 527-1/-2	%	1.7 / 2.3
Flexural modulus, ISO 178	2 mm/min	ISO 178	MPa	11000 / -
Flexural strength, ISO 178	2 mm/min	ISO 178	MPa	220 / -
Charpy impact strength, +23°C	+23°C	ISO 179/1eU	kJ/m ²	37 / 40
Charpy impact strength, -30°C	-30°C	ISO 179/1eU	kJ/m ²	30 / -
Charpy notched impact strength, +23°C	+23°C	ISO 179/1eA	kJ/m ²	9 / 13

*: **conditioned according to ISO 1110**

	Condition	Standard	Unit	Value
Thermal properties				
Melting temperature, 10°C/min		ISO 11357-1	°C	222
Temp. of deflection under load, 1.80 MPa	1.80 MPa	ISO 75	°C	197

	Condition	Standard	Unit	Value
Burning behaviour				
Flammability, 0.75 mm	0.75 mm	UL 94		V0
Flammability, 1.5 mm	1.5 mm	UL 94		V0
Flammability, 3.0 mm	3.0 mm	UL 94		V0
Glow-wire flammability index, GWFI, 0.75 mm	0.75 mm	IEC 60695-2-12	°C	960
Glow-wire flammability index, GWFI, 1.5 mm	1.5 mm	IEC 60695-2-12	°C	960
Glow-wire ignition temperature, GWIT, 0.75 mm	0.75 mm	IEC 60695-2-13	°C	825
Glow-wire ignition temperature, GWIT, 1.5 mm	1.5 mm	IEC 60695-2-13	°C	850
Burning rate, FMVSS, Thickness 1 mm		FMVSS 302		<100 mm/min


	Condition	Standard	Unit	Value
Electrical properties				
Comparative tracking index	Solution A	IEC 60112	V	450.0

Processing conditions

Drying temperature/time	75-85°C / 2-4h (with dew point of dried air < -30 °C)
Suggested max moisture	0.12 %
Rear temperature	230 - 240 °C
Middle temperature	240 - 250 °C
Front temperature	240 - 255 °C
Recommended mould temperature	80 - 100 °C


Stress-strain, dry

Temperature (°C)



Stress-strain, conditioned

Temperature (°C)



Injection notes

The material is supplied in airtight bags, ready for use. In case that the virgin material has absorbed moisture, it must be dried with a dehumidified air drying equipment, dew point minimum -20°C. Recommended time 2-4h.

Injection advice

All reinforced, flame retardant compounds generate some level of abrasion/corrosion to the steel processing equipment. These issues may be magnified by using incorrect processing conditions (temperatures, residence time, moisture level ...) during the moulding process. Therefore, Domo recommends you adhere to the processing conditions detailed in this technical data sheet. For equipment that comes into contact with molten flame retardant compounds, Domo advises you to use a steel with high chromium and high carbon content (having a minimum concentration of 16% chromium) to prevent corrosion and abrasion. For the correct reference of steel associated to flame retardant compounds' processing, please refer to your equipment manufacturers. In the case of high requirements on surface quality a mould temperature of up to 120°C can be considered. The processing parameters like processing temperatures are a recommendation and can be adjusted in function of injection machine size, part geometry / design.