

TECHNICAL DATA SHEET

TECHNYL PROTECT C 50H2 GY 271N

TECHNYL PROTECT C 50H2 GY 271N is an unreinforced polyamide 6 based on a non-phosphorous and non-halogenated flame retardant system, heat stabilized, for injection moulding. This product, UL94 VO @ 0,4mm, offers excellent moldability together with good stiffness.

General

Certifications	RoHS EC 1907/2006 (REACH)	UL listed product
Polymer type	PA6	
Feature	halogen free flame retardant	heat resistant
Applications	electrical/electronic applications	
Colors available	grey	
Forms	pellets	
Processing technology	injection moulding	

Product identification

ISO 1043 abbreviation	PA6,FR(30)
ISO 16396 designation	PA6,0FR(30)0,M1,S14-030

Condition	Standard	Unit	Value
-----------	----------	------	-------

Physical properties

Condition	Standard	Unit	Value
Density	ISO 1183	g/cm ³	1.16
Water absorption	24 hr, 23°C ISO 62	%	1.1
Molding shrinkage, parallel	ISO 294-4, 2577	%	0.7 - 0.9
Molding shrinkage, normal	ISO 294-4, 2577	%	0.6 - 0.8

	Condition	Standard	Unit	Value
Mechanical properties				dam / cond.*
Tensile modulus	1mm/min	ISO 527-1/-2	MPa	3500 / 1250
Stress at break		ISO 527-1/-2	MPa	60 / 45
Strain at break		ISO 527-1/-2	%	8 / 12
Flexural modulus, ISO 178	2 mm/min	ISO 178	MPa	3150 / -
Flexural strength, ISO 178	2 mm/min	ISO 178	MPa	200 / 70
Charpy notched impact strength, +23°C	+23°C	ISO 179/1eA	kJ/m ²	2.5 / 10

***: conditioned according to ISO 1110**

	Condition	Standard	Unit	Value
Thermal properties				
Melting temperature, 10°C/min		ISO 11357-1	°C	222
Temp. of deflection under load, 0.45 MPa	0.45 MPa	ISO 75	°C	180
Temp. of deflection under load, 1.80 MPa	1.80 MPa	ISO 75	°C	75
Vicat softening temperature	50°C/h - 50N	ISO 306	°C	205

Condition	Standard	Unit	Value
-----------	----------	------	-------

Burning behaviour

Condition	Standard	Unit	Value
UL Yellow Card availability 1	Click here to have access to the UL Yellow Card availability 1 -> QMFZ2.E44716		
Flammability, 0.40 mm	0.40 mm	UL 94	V0
Flammability, 0.75 mm	0.75 mm	UL 94	V0
Flammability, 1.5 mm	1.5 mm	UL 94	V0
Flammability, 3.0 mm	3.0 mm	UL 94	V0
Glow-wire flammability index, GWFI, 0.75 mm	0.75 mm	IEC 60695-2-12	°C 960
Glow-wire flammability index, GWFI, 1.5 mm	1.5 mm	IEC 60695-2-12	°C 960
Glow-wire flammability index, GWFI, 3.0 mm			°C 960
Glow-wire ignition temperature, GWIT, 0.75 mm	0.75 mm	IEC 60695-2-13	°C 700
Glow-wire ignition temperature, GWIT, 1.5 mm	1.5 mm	IEC 60695-2-13	°C 700
Glow-wire ignition temperature, GWIT, 3.0 mm	3.0 mm	IEC 60695-2-13	°C 700
Oxygen index			% 36.0
Burning rate, FMVSS, Thickness 1 mm		FMVSS 302	<100

Condition	Standard	Unit	Value
-----------	----------	------	-------

Electrical properties

Condition	Standard	Unit	Value
Volume resistivity		IEC 62631-3-1	ohm.m 1.0E13
Surface resistivity		IEC 62631-3-1	ohm 1.0E15
Comparative tracking index	Solution A	IEC 60112	V 600.0
CTI performance level category		Sol A	PLC 0
Dielectric strength	1 mm	IEC 60243-1	kV/mm 34.0

Processing conditions

Drying temperature/time	80
-------------------------	----

Processing conditions

Suggested max moisture	0.02 %
Rear temperature	230 - 235 °C
Middle temperature	235 - 240 °C
Front temperature	235 - 245 °C
Recommended mould temperature	60 - 90 °C

Injection notes

The material is supplied in airtight bags, ready for use. In case that the virgin material has absorbed moisture, it must be dried with a dehumidified air drying equipment, dew point minimum -20°C. Recommended time 2-4h.

Injection advice

All reinforced, flame retardant compounds generate some level of abrasion/corrosion to the steel processing equipment. These issues may be magnified by using incorrect processing conditions (temperatures, residence time, moisture level ...) during the moulding process. Therefore, Domo recommends you adhere to the processing conditions detailed in this technical data sheet. For equipment that comes into contact with molten flame retardant compounds, Domo advises you to use a steel with high chromium and high carbon content (having a minimum concentration of 16% chromium) to prevent corrosion and abrasion. For the correct reference of steel associated to flame retardant compounds' processing, please refer to your equipment manufacturers. In the case of high requirements on surface quality a mould temperature of up to 120°C can be considered. The processing parameters like processing temperatures are a recommendation and can be adjusted in function of injection machine size, part geometry / design.