

EXPERIMENTAL DATASHEET

TECHNYL SAFE C 216WFC V50 BK

TECHNYL SAFE C 216WFC V50 BK is a polyamide 6, 50% glass fibre reinforced, food contact and drinking water approved, for injection moulding. Designed to be used in moulded part requiring improved stiffness, dimensional stability and hydrolysis resistance versus PA6GF30 in consumer & industrial goods as well as appliances in contact with drinking water. WRAS approval at 85°C.

General

Certifications	Food contact EU RoHS WRAS	Food contact FDA EC 1907/2006 (REACH)
Polymer type	PA6	
Feature	food contact approved good stiffness	drinking water contact approved(obs)
Applications	small appliance industrial applications	consumer applications large appliance
Colors available	black	natural
Forms	pellets	
Processing technology	injection moulding	

Product identification

ISO 1043 abbreviation	PA6-GF50
ISO 16396 designation	PA6,GF50,M1,S14-160

EXPERIMENTAL DATASHEET

TECHNYL SAFE C 216WFC V50 BK

	Condition	Standard	Unit	Value
Physical properties				
Density		ISO 1183	g/cm ³	1.56
Humidity absorption	T=23°C, 50% RH	ISO 62	%	1.7
Molding shrinkage, parallel		ISO 294-4, 2577	%	0.25 - 0.45
Molding shrinkage, normal		ISO 294-4, 2577	%	0.9 - 1.1
Melt volume-flow rate, MVR, 5.0 kg	275°C, 5kg	ISO 1133	cm ³ /10 min	15.0
Viscosity number	96% H2SO4	ISO 307	cm ³ /g	145.0

	Condition	Standard	Unit	Value
Mechanical properties				dam / cond.*
Tensile modulus	1 mm/min	ISO 527-1/-2	MPa	16500 / 9300
Stress at break		ISO 527-1/-2	MPa	235 / 150
Strain at break		ISO 527-1/-2	%	3 / 6
Flexural modulus, ISO 178	2 mm/min	ISO 178	MPa	12500 / 9100
Charpy impact strength, +23°C	+23°C	ISO 179/1eU	kJ/m ²	95 / 105
Charpy impact strength, -30°C	-30°C	ISO 179/1eU	kJ/m ²	100 / 105
Charpy notched impact strength, +23°C	+23°C	ISO 179/1eA	kJ/m ²	20 / 30
Charpy notched impact strength, -30°C	-30°C	ISO 179/1eA	kJ/m ²	16 / 17

*: **conditioned according to ISO 1110**

	Condition	Standard	Unit	Value
Thermal properties				
Melting temperature, 10°C/min		ISO 11357-1	°C	221

Condition	Standard	Unit	Value
-----------	----------	------	-------

Burning behaviour

Burning rate, FMVSS, Thickness 1 mm		FMVSS 302		<100 mm/min
-------------------------------------	--	-----------	--	-------------

Processing conditions

Drying temperature/time	75-85°C / 2-4h (with dew point of dried air < -30 °C)
Rear temperature	250 - 270 °C
Middle temperature	260 - 280 °C
Front temperature	260 - 290 °C
Recommended melt temperature	250 - 290 °C
Recommended mould temperature	80 - 100 °C