

TECHNICAL DATA SHEET

TECHNYL SAFE C 116FC NC
DOMAMID 6LVFC NC



TECHNYL SAFE C 116FC NC is a polyamide 6, unfilled, improved flowability, food contact approved for injection moulding. Designed to be used for food contact in industrial consumer good as well as appliance applications.

General

Polymer type	PA6	
Certifications	Food contact EU	RoHS
Feature	food contact approved	high flow
Applications	small appliance industrial applications building / construction	consumer applications large appliance
Colors available	natural	
Forms	pellets	
Processing technology	injection moulding	

Product identification

ISO 1043 abbreviation	PA6
ISO 16396 designation	PA6,M,S12-030

Condition	Standard	Unit	Value
-----------	----------	------	-------

Physical properties

	Condition	Standard	Unit	Value
Density		ISO 1183	g/cm ³	1.14
Molding shrinkage, parallel		ISO 294-4, 2577	%	0.9 - 1.1
Molding shrinkage, normal		ISO 294-4, 2577	%	1.0 - 1.2
Melt volume-flow rate, MVR, 5.0 kg	275°C, 5kg	ISO 1133	cm ³ /10 min	225.0
Viscosity number	96% H2SO4	ISO 307	cm ³ /g	125.0

	Condition	Standard	Unit	Value
Mechanical properties				dam / cond.*
Tensile modulus	1 mm/min	ISO 527-1/-2	MPa	3100 / -
Strain at break	50 mm/min	ISO 527-1/-2	%	50 / -
Yield stress	50 mm/min	ISO 527-1/-2	MPa	80 / -
Flexural modulus, ISO 178	2 mm/min	ISO 178	MPa	2700 / -
Flexural strength, ISO 178	2 mm/min	ISO 178	MPa	100 / -
Charpy impact strength, +23°C	+23°C	ISO 179/1eU	kJ/m ²	NB
Charpy notched impact strength, +23°C	+23°C	ISO 179/1eA	kJ/m ²	4 / -
Izod impact strength, +23°C	+23°C	ISO 180/1U	kJ/m ²	NB
Izod notched impact strength, +23°C	+23°C	ISO 180/1A	kJ/m ²	4 / -
Rockwell hardness		ISO 2039/2	ScaleR	120 / -

*: **conditioned according to ISO 1110**

	Condition	Standard	Unit	Value
Thermal properties				
Melting temperature, 10°C/min		ISO 11357-1	°C	221
Temp. of deflection under load, 0.45 MPa	0.45 MPa	ISO 75	°C	180
Temp. of deflection under load, 1.80 MPa	1.80 MPa	ISO 75	°C	70
Vicat softening temperature	50°C/h - 50N	ISO 306	°C	205

Condition	Standard	Unit	Value
-----------	----------	------	-------

Burning behaviour

Flammability, 0.75 mm	0.75 mm	UL 94		V2
Flammability, 1.5 mm	1.5 mm	UL 94		V2
Flammability, 3.0 mm	3.0 mm	UL 94		V2
Glow-wire flammability index, GWFI, 3.0 mm			°C	850
Glow-wire flammability index, GWFI	1-3 mm	IEC 60695-2-12	°C	>= 850
Glow-wire ignition temperature, GWIT	1-3 mm	IEC 60695-2-13	°C	725
Burning rate, FMVSS, Thickness 1 mm		FMVSS 302		< 100 mm/min

Condition	Standard	Unit	Value
-----------	----------	------	-------

Electrical properties

Volume resistivity		IEC 62631-3-1	ohm.m	1.0E13
Surface resistivity		IEC 62631-3-1	ohm	1.0E13
Comparative tracking index	Solution A	IEC 60112	V	600.0
CTI performance level category		Sol A		PLC 0

Processing conditions

Drying temperature/time	75-85°C / 2-4h (with dew point of dried air < -30 °C)			
Suggested max moisture	0.2 %			
Recommended melt temperature	230 - 250 °C			
Recommended mould temperature	40 - 80 °C			

Injection notes

The material is supplied in airtight bags, ready for use. In case that the virgin material has absorbed moisture, it must be dried with a dehumidified air drying equipment, dew point minimum -20°C. Recommended time 2-4h.

Injection advice

For reinforced polyamides, Domo recommends the use of steel with a high content of carbon, and purified for polishing, to avoid or limit the abrasion. For example: X38CrMoV5-1 (EN Norm) - 1.2367 / 1.2343 (DIN Norm) or X160CrMoV12 (EN Norm) - 1.2601 / 1.2379 (DIN Norm). In the case of high requirements on surface quality a mould temperature of up to 120°C can be considered. The processing parameters like processing temperatures are a recommendation and can be adjusted in function of injection machine size, part geometry / design.