

EXPERIMENTAL DATASHEET

TECHNYL SAFE C 216WFC V50 NC

TECHNYL SAFE C 216WFC V50 NC is a polyamide 6, 50% glass fibre reinforced, food contact and drinking water approved, for injection moulding. Designed to be used in moulded part requiring improved stiffness, dimensional stability and hydrolysis resistance versus PA6GF30 in consumer & industrial goods as well as appliances in contact with drinking water. WRAS approval at 85°C.

General

| | | |
|-----------------------|--|--|
| Certifications | Food contact EU RoHS WRAS | Food contact FDA EC 1907/2006 (REACH) |
| Polymer type | PA6 | |
| Feature | food contact approved good stiffness | drinking water contact approved(obs) |
| Applications | small appliance industrial applications | consumer applications large appliance |
| Colors available | black | natural |
| Forms | pellets | |
| Processing technology | injection moulding | |

Product identification

| | |
|-----------------------|---------------------|
| ISO 1043 abbreviation | PA6-GF50 |
| ISO 16396 designation | PA6,GF50,M1,S14-160 |

EXPERIMENTAL DATASHEET

TECHNYL SAFE C 216WFC V50 NC

| | Condition | Standard | Unit | Value |
|------------------------------------|----------------|-----------------|-------------------------|-------------|
| Physical properties | | | | |
| Density | | ISO 1183 | g/cm ³ | 1.56 |
| Humidity absorption | T=23°C, 50% RH | ISO 62 | % | 1.7 |
| Molding shrinkage, parallel | | ISO 294-4, 2577 | % | 0.25 - 0.45 |
| Molding shrinkage, normal | | ISO 294-4, 2577 | % | 0.9 - 1.1 |
| Melt volume-flow rate, MVR, 5.0 kg | 275°C, 5kg | ISO 1133 | cm ³ /10 min | 15.0 |
| Viscosity number | 96% H2SO4 | ISO 307 | cm ³ /g | 145.0 |

| | Condition | Standard | Unit | Value |
|---------------------------------------|-----------|--------------|-------------------|---------------------|
| Mechanical properties | | | | dam / cond.* |
| Tensile modulus | 1 mm/min | ISO 527-1/-2 | MPa | 16500 / 9300 |
| Stress at break | 5 mm/min | ISO 527-1/-2 | MPa | 235 / 150 |
| Strain at break | 5 mm/min | ISO 527-1/-2 | % | 3 / 6 |
| Flexural modulus, ISO 178 | 2 mm/min | ISO 178 | MPa | 12500 / 9100 |
| Charpy impact strength, +23°C | +23°C | ISO 179/1eU | kJ/m ² | 95 / 105 |
| Charpy impact strength, -30°C | -30°C | ISO 179/1eU | kJ/m ² | 100 / 105 |
| Charpy notched impact strength, +23°C | +23°C | ISO 179/1eA | kJ/m ² | 20 / 30 |
| Charpy notched impact strength, -30°C | -30°C | ISO 179/1eA | kJ/m ² | 16 / 17 |

*: **conditioned according to ISO 1110**

| | Condition | Standard | Unit | Value |
|-------------------------------|-----------|-------------|------|-------|
| Thermal properties | | | | |
| Melting temperature, 10°C/min | | ISO 11357-1 | °C | 221 |

| Condition | Standard | Unit | Value |
|-----------|----------|------|-------|
|-----------|----------|------|-------|

Burning behaviour

| | | | |
|-------------------------------------|--|-----------|--------------|
| Burning rate, FMVSS, Thickness 1 mm | | FMVSS 302 | < 100 mm/min |
|-------------------------------------|--|-----------|--------------|

Processing conditions

| | |
|-------------------------------|---|
| Drying temperature/time | 75-85°C / 2-4h (with dew point of dried air < -30 °C) |
| Rear temperature | 250 - 270 °C |
| Middle temperature | 260 - 280 °C |
| Front temperature | 260 - 290 °C |
| Recommended melt temperature | 250 - 290 °C |
| Recommended mould temperature | 80 - 100 °C |