

TECHNICAL DATA SHEET

**TECHNYL STAR S 60X2 V30 BK 1N**  
**TECHNYL STAR XS 1680 BLACK 1N**



TECHNYL STAR S 60X2 V30 BK 1N is a grade based on a non-halogenated flame retardant system and on a patented high flow polyamide 6 resin (Technyl Star), reinforced of 30% of glass fiber, heat stabilized, for injection moulding. This grade is heat stabilized, provides optimized injection moulding performance and blooming reduction.

**General**

Polymer type	PA6	
Certifications	RoHS EC 1907/2006 (REACH)	UL listed product
Feature	halogen and red phosphorus free flame retardant excellent surface finish very high flow	corrosion resistant low temperature impact resistant
Applications	connectors	electrical/electronic applications
Colors available	black	
Forms	pellets	
Processing technology	injection moulding	

**Product identification**

ISO 1043 abbreviation	PA6-GF30 FR(40)
ISO 16396 designation	PA6,GF30FR(40),M,S14-110

Condition	Standard	Unit	Value
-----------	----------	------	-------

**Physical properties**

	Condition	Standard	Unit	Value
Density		ISO 1183	g/cm <sup>3</sup>	1.42
Water absorption	24 hr, 23°C	ISO 62	%	0.8 - 0.9
Water absorption, saturation			%	4.0
Molding shrinkage, parallel		ISO 294-4, 2577	%	0.25 - 0.3
Molding shrinkage, normal		ISO 294-4, 2577	%	0.85 - 0.9

	Condition	Standard	Unit	Value
<b>Mechanical properties</b>				<b>dam / cond.*</b>
Tensile modulus	1mm/min	ISO 527-1/-2	MPa	11000 / 7700
Stress at break	5mm/min	ISO 527-1/-2	MPa	150 / 95
Strain at break		ISO 527-1/-2	%	2.5 / 4.4
Flexural modulus, ISO 178	2 mm/min	ISO 178	MPa	9500 / 6700
Flexural strength, ISO 178	2 mm/min	ISO 178	MPa	225 / 160
Charpy impact strength, +23°C	+23°C	ISO 179/1eU	kJ/m <sup>2</sup>	65 / 62
Charpy notched impact strength, +23°C	+23°C	ISO 179/1eA	kJ/m <sup>2</sup>	10 / 9

\*: **conditioned according to ISO 1110**

	Condition	Standard	Unit	Value
<b>Thermal properties</b>				
Melting temperature, 10°C/min		ISO 11357-1	°C	220
Temp. of deflection under load, 1.80 MPa	1.80 MPa	ISO 75	°C	205

	Condition	Standard	Unit	Value
<b>Burning behaviour</b>				
UL Yellow Card availability 1	<b><u><a href="#">Click here to have access to the UL Yellow Card availability 1 -&gt; QMFZ2.E44716</a></u></b>			
Flammability, 0.75 mm	0.75 mm	UL 94		V0
Flammability, 1.5 mm	1.5 mm	UL 94		V0
Flammability, 3.0 mm	3.0 mm	UL 94		V0
Glow-wire flammability index, GWFI, 0.75 mm	0.75 mm	IEC 60695-2-12	°C	960
Glow-wire flammability index, GWFI, 1.5 mm	1.5 mm	IEC 60695-2-12	°C	960
Glow-wire flammability index, GWFI, 3.0 mm			°C	960
Burning rate, FMVSS, Thickness 1 mm		FMVSS 302		< 100 mm/min

	Condition	Standard	Unit	Value
<b>Electrical properties</b>				
Volume resistivity		IEC 62631-3-1	ohm.m	1.0E13
Surface resistivity		IEC 62631-3-1	ohm	6.0E14
Comparative tracking index	Solution A	IEC 60112	V	600.0
CTI performance level category		Sol A		PLC 0
Dielectric strength	1 mm	IEC 60243-1	kV/mm	38.0

### Processing conditions

Drying temperature/time	80 °C
Suggested max moisture	0.1 %
Rear temperature	240 - 245 °C
Middle temperature	245 - 255 °C
Front temperature	255 - 260 °C
Recommended mould temperature	60 - 90 °C

### Injection notes

The material is supplied in airtight bags, ready for use. In case that the virgin material has absorbed moisture, it must be dried with a dehumidified air drying equipment, dew point minimum -20°C. Recommended time 2-4h.

### Injection advice

All reinforced, flame retardant compounds generate some level of abrasion/corrosion to the steel processing equipment. These issues may be magnified by using incorrect processing conditions (temperatures, residence time, moisture level ...) during the moulding process. Therefore, Domo recommends you adhere to the processing conditions detailed in this technical data sheet. For equipment that comes into contact with molten flame retardant compounds, Domo advises you to use a steel with high chromium and high carbon content (having a minimum concentration of 16% chromium) to prevent corrosion and abrasion. For the correct reference of steel associated to flame retardant compounds' processing, please refer to your equipment manufacturers. In the case of high requirements on surface quality a mould temperature of up to 120°C can be considered. The processing parameters like processing temperatures are a recommendation and can be adjusted in function of injection machine size, part geometry / design.