



HDPE for LiBS Seperator

YUHWA HIDDEN VH095

Features
and Uses

Properties

Application	HDPE for LiBS Seperator		
Features	Good property & Processibility balance		
Uses	LiBS of wet process (Lithium 2nd Battery Separator)		
Items	Specification	Unit	Test Method
Average Mv (10° g/mol)	0.4	—	KPIC Method
Density	0.95	g/cm³	ASTM D1505
Bulk Density	0.46	g/cm³	ISO 60
Avg. Particle Size	125	μm	KPIC Method
Melting Point	135	°C	ASTM D3418