



General Homo PP for Film

YUHWA POLYPRO 1088B

Features
and Uses

Properties

Application	General Homo PP for Film		
Features	IPP, High Slippery		
Uses	Food Packaging, Clothes Packaging, General Packaging		
Items	Specification	Unit	Test Method
Melt Index	10	g/10min.	ASTM D1238
Density	0.9	g/cm³	ASTM D1505
Mold Shrinkage	1.1~2.0	%	KPIC Method
Water Absorption	<0.01	%	ASTM D570
Tensile Strength at Yield	360	kgf/cm²	ASTM D638
Elongation at Break	>500	%	ASTM D638
Flexural Modulus	16,000	kgf/cm²	ASTM D790
Hardness (Rockwell)	100	R Scale	ASTM D785
Impact Strength (Izod with Notch)	4	kgf cm/cm	ASTM D256
Melting Point	163	℃	ASTM D3418
Softening Point (Vicat)	152	℃	ASTM D1525
Heat Deflection Temperature	110	℃	ASTM D648