



High Purity PP for Capacitor Film

YUHWA POLYPRO 5014L HPT-H

Features
and Uses

Properties

Application	High Purity PP for Capacitor Film			
Features	IOPP, Ultra High Purity, Rough-surface Film			
Uses	Capacitor Film (Roughness)			
Items	Specification	Unit	Test Method	
Melt Index	3.8	g/10min.	ASTM D1238	
Density	0.9	g/cm³	ASTM D1505	
Catalyst residue, Al (XRF)	2~4	ppm	KPIC Method	
Catalyst residue, Cl (XRF)	1~3	ppm	KPIC Method	
Total Ash Content (XRF)	10~20	ppm	KPIC Method	
Isotactic Index	96	%	KPIC Method	
Melting Point	162~165	℃	ASTM D3418	
Dielectric Constant	2.25	—	KPIC Method	