



HSPB Block Copolymer for Injection

YUHWA POLYPRO SB9230

Features
and Uses

Properties

Application	HSPB Block Copolymer for Injection			
Features	High Gloss, High Flowability, Impact Resistance, High Stiffness, All Color 94HB			
Uses	Interior Trims for Automobile Parts, PP Compound Base Resin			
	Items	Specification	Unit	Test Method
	Melt Index	30	g/10min.	ASTM D1238
	Density	0.91	g/cm ³	ASTM D1505
	Mold Shrinkage	1.4~1.8	%	KPIC Method
	Tensile Strength at Yield	290	kgf/cm ²	ASTM D638
	Elongation at Break	>200	%	ASTM D638
	Flexural Modulus	15,000	kgf/cm ²	ASTM D790
	Hardness (Rockwell)	98	R Scale	ASTM D785
	Impact Strength (Izod with Notch) 25°C	10	kgf cm/cm	ASTM D256
	Impact Strength (Izod with Notch) -20°C	3	kgf cm/cm	ASTM D256
	Melting Point	167	°C	ASTM D3418
	Softening Point (Vicat)	152	°C	ASTM D1525
	Heat Deflection Temperature	131	°C	ASTM D648