

LUVOCOM® 1200-7116-1

Acrylo butadiene styrene
with carbon fibers, black

Physical properties		Test method	Specimen	Units	Typical value
Specific gravity		ISO 1183-3		g/cm ³	1,09
Water absorption	23°C / 24h	ISO 62	ISO 3167 A	%	< 0,3
Melt volume rate (MVR)		220°C / 10kg	pellet	cm ³ /10 min	14
Linear mould shrinkage		DIN 16742	ISO 3167 A	%	0,2-0,4

Mechanical properties at 23°C / 50% rh					
Tensile strength	dry, @50 mm/min	ISO 527	ISO 3167 A	MPa	90
Elongation @Fmax.	dry, @50 mm/min	ISO 527	ISO 3167 A	%	1,5
Tensile modulus	dry, @1 mm/min	ISO 527	ISO 3167 A	GPa	8
Flexural strength	dry, @10 mm/min	ISO 178	ISO 3167 A	MPa	130
Flexural elongation @Fmax.	dry, @10 mm/min	ISO 178	ISO 3167 A	%	1,9
Flexural modulus	dry, @2 mm/min	ISO 178	ISO 3167 A	GPa	6
Impact strength	dry	ISO 179 1eU	80x10x4mm	kJ/m ²	18
Impact strength, notched	dry	ISO 179 1eA	80x10x4mm	kJ/m ²	6

Thermal properties					
Vicat softening temp.	VST A	DIN ISO 306	ISO 3167 A	°C	100
Heat distortion temp.	HDT A	ISO 75	80x10x4mm	°C	96
Continuous service temp.	20.000 h	IEC 60216	ISO 3167 A	°C	60
Service temperature	during lifetime max. 200h		ISO 3167 A	°C	80
CLTE, longitudinal		ISO 11359	10x8x4 mm	10 ⁻⁵ /K	4

Electrical properties					
Insulation resistance	strip electrode R25	DIN EN 62631-3-3	ISO 3167 A	Ω	≤10 ³
Surface resistance	ROB	DIN EN 62631-3-2	Ronde 60x4mm	Ω	<10 ⁴

Main features

Electrically conductive, suitable for continuous discharging of statically-generated electricity. Strong, stiff parts.

Acrylo butadiene styrene
with carbon fibers, black

Recommended processing parameters

Delivery form & storage

Unless indicated otherwise, the material is delivered as 3mm long pellets in sealed bags on pallets. Preferably storage should be effected in dry and normally temperatured rooms.

Predrying

It is advisable to predry the granules with a suitable dryer immediately before processing. The granule may absorb moisture from the environment.

Dryer type	Temperature °C	Drying time in h
Dehumidifying dryer	70 - 95	2 - 4

Recommended processing parameters

In general this product can be processed on conventional injection moulding machines while observing the usual technical guidelines. Any added fibrous materials or fillers may have an abrasive effect. In this case the cylinder and screw should be protected against wear as is usual in the processing of reinforced thermoplastic materials. Lengthy dwell times for the melts in the cylinder should be avoided. Lower the temperatures during interruptions!

Mold	Melt temperature	Nozzle	Zone 3	Zone 2	Zone 1
40 - 80 °C	230 - 60 °C	220 - 250 °C	230 - 260 °C	220 - 250 °C	220 - 250 °C

Additional information

During processing, the moisture content should not exceed 0.1%. Moisture may lead to smearing and in extreme cases to foaming. Usually the material can be processed over a broad temperature range and can thus be adapted to a wide variety of processing conditions. Temperatures >270°C may lead to thermal damage. The processing notes provided merely represent a recommendation for general use. Due to the large variety of machines, geometries and volumes of parts, etc., it may be necessary to employ different settings according to the specific application. Please contact us for further information.