

Polyamide 46

with aramid reinforcement and PTFE, heat stabilized, natural color (beige)

Physical properties		Test method	Specimen	Units	Typical value
Specific gravity		ISO 1183-3		g/cm ³	1,4
Water absorption	23°C / 24h	ISO 62	ISO 3167 A	%	<1,0
Linear mould shrinkage		DIN 16742	ISO 3167 A	%	1,3-2,0

Mechanical properties at 23°C / 50% rh

Tensile strength	dry, @50 mm/min	ISO 527	ISO 3167 A	MPa	65
Elongation @Fmax.	dry, @50 mm/min	ISO 527	ISO 3167 A	%	5
Tensile modulus	dry, @1 mm/min	ISO 527	ISO 3167 A	GPa	2,9
Flexural strength	dry, @10 mm/min	ISO 178	ISO 3167 A	MPa	95
Flexural elongation @Fmax.	dry, @10 mm/min	ISO 178	ISO 3167 A	%	6,5
Flexural modulus	dry, @2 mm/min	ISO 178	ISO 3167 A	GPa	2,6
Impact strength	dry	ISO 179 1eU	80x10x4mm	kJ/m ²	32

Thermal properties

Continuous service temp.	20.000 h	IEC 60216	ISO 3167 A	°C	150
Service temperature	during lifetime max. 200h		ISO 3167 A	°C	160

Electrical properties

Insulation resistance	strip electrode R25	DIN EN 62631-3-3	ISO 3167 A	Ω	>10 ¹²
-----------------------	---------------------	------------------	------------	---	-------------------

Tribological properties

CoF - Block on Ring	100Cr6, 2 MPa, 1 m/s	ASTM G137	molded sample		0,31
Sp. Wear Rate-Block on Ring	100Cr6, 2 MPa, 1 m/s	ASTM G137	molded sample	10 ⁻⁶ mm ³ /Nm	0,3

Main features

Good friction and wear behaviour especially at high temperatures. Low warpage.

Polyamide 46

with aramid reinforcement and PTFE, heat stabilized, natural color (beige)

Recommended processing parameters

Delivery form & storage

Unless indicated otherwise, the material is delivered as 3mm long pellets in sealed bags on pallets. Preferably storage should be effected in dry and normally temperatured rooms.

Predrying

Due to moisture absorption from the environment, pre-drying of the material is recommended. Moisture could lead to molecular degradation and surface defects (e.g. smearing). Excessively high predrying temperatures may cause discoloration. Recommended moisture content before processing: <0.05%

Dryer type	Temperature °C	Drying time in h
Dehumidifying dryer	80	2 - 8
Vacuum Dryer	80	2 - 12

Recommended processing parameters

In general this product can be processed on conventional injection moulding machines while observing the usual technical guidelines. Any added fibrous materials or fillers may have an abrasive effect. In this case the cylinder and screw should be protected against wear as is usual in the processing of reinforced thermoplastic materials. Lengthy dwell times for the melts in the cylinder should be avoided. Lower the temperatures during interruptions!

Mold	Melt temperature	Nozzle	Zone 3	Zone 2	Zone 1
90 - 130 °C	310 °C	290 - 320 °C	300 - 320 °C	285 - 315 °C	285 - 310 °C

Additional information

The melt residence time of this material should not exceed 4 minutes. Due to the fast crystallization of this product a high injection speed is recommended. A good mold venting is required to avoid burned marks (diesel effect). For a better surface finish, best mechanical performance and stable dimensional parts, a mold temperature on the higher side (up to 150 °C) is recommended. Processing temperatures above 330°C may very rapidly cause thermal damage and should therefore be avoided. The processing notes provided merely represent a recommendation for general use. Due to the large variety of machines, geometries and volumes of parts, etc., it may be necessary to employ different settings according to the specific application. Please contact us for further information.