

LARTON K/40 HM

Compound based on Polyphenylene Sulphide (PPS). Carbon fibers. Intrinsically flame retardant. High tensile modulus. Very good chemical resistance. Very good thermal properties. Low smoke density and low toxicity index. PFAS-free product.

The products mentioned herein are not suitable for applications in contact with foodstuffs or for potable water transportation, or for toy manufacturing.

The products mentioned herein are not suitable for applications in the pharmaceutical, medical or dental sector.

PHYSICAL PROPERTIES	STANDARD	VALUE MEASURE UNITS
Density	ISO 1183	1.50 g/cm ³
Linear shrinkage at moulding		
Longitudinal (0.078in/8,700psi)	ISO 294-4	0.05 ÷ 0.15 %
Transversal (0.078in/8,700psi)	ISO 294-4	0.35 ÷ 0.55 %
Dimensional stability	---	65
Moisture absorption		
saturation, in air	ISO 62-4	0.02 %
MECHANICAL PROPERTIES	STANDARD	VALUE MEASURE UNITS
CHARPY impact strength		
Unnotched, at 23°F	ISO 179-1eU	4.5 ft.lb/in ²
Notched, at +23°F	ISO 179-1eA	1.6 ft.lb/in ²
MECHANICAL PROPERTIES	STANDARD	VALUE MEASURE UNITS
Tensile elongation		
At break (0.196 in/min), 23°F	ISO 527	0.5 %
At break (0.196 in/min), 60°F	ISO 527	0.5 %
At break (0.196 in/min), 90°F	ISO 527	1.0 %
At break (0.196 in/min), 120°F	ISO 527	1.0 %
At break (0.196 in/min), 150°F	ISO 527	1.0 %
Tensile strength		
At break (0.196 in/min), 23°F	ISO 527	25500 psi
At break (0.196 in/min), 60°F	ISO 527	18000 psi
At break (0.196 in/min), 90°F	ISO 527	16500 psi
At break (0.196 in/min), 120°F	ISO 527	10500 psi
At break (0.196 in/min), 150°F	ISO 527	9000 psi
Elastic modulus		
Tensile (0.04 in/min), 23°F	ISO 527	5100 kpsi
Tensile (0.04 in/min), 60°F	ISO 527	4200 kpsi
Tensile (0.04 in/min), 90°F	ISO 527	2400 kpsi
Tensile (0.04 in/min), 120°F	ISO 527	1800 kpsi
Tensile (0.04 in/min), 150°F	ISO 527	1395 kpsi

LARTON K/40 HM

THERMAL PROPERTIES	STANDARD	VALUE MEASURE UNITS
Coefficient of linear thermal expansion (CLTE)		
30°F to 100°F (longitudinal)	ISO 11359	2 × 10 ⁻⁶ K ⁻¹
30°F to 100°F (transversal)	ISO 11359	20 × 10 ⁻⁶ K ⁻¹
VICAT - Softening point		
11 lb (heating rate 250°F/h)	ISO 306	491 °F
HDT - Heat Deflection Temperature		
66 psi	ISO 75	536 °F
264 psi	ISO 75	518 °F
Thermal conductivity		
in plane	ASTM E 1461-92	5.2 W/(m·K)
through plane	ASTM E 1461-92	2.4 W/(m·K)
FLAMMABILITY	STANDARD	VALUE MEASURE UNITS
Flammability rating		
0.125 in. thickness	UL 94	V-0
0.060 in. thickness	UL 94	V-0
0.030 in. thickness	UL 94	V-0
GWFI - Glow Wire Flammability Index		
0.078 in. thickness	IEC 60695-2-12	960 °C
0.040 in. thickness	IEC 60695-2-12	960 °C
GWIT - Glow Wire Ignition Test		
0.078 in. thickness	IEC 60695-2-13	775 °C
0.040 in. thickness	IEC 60695-2-13	775 °C
ELECTRICAL PROPERTIES	STANDARD	VALUE MEASURE UNITS
Electrical resistivity		
surface, dry	ASTM D 257 / D 4496	5E1 ohm
volume	ASTM D 257 / ASTM D4496	1E2 ohm.cm
Dielectric strength (short period)		
0.078 in. thickness, 73°F, dry	ASTM D 149	51 kV/mm

STORAGE

Best storage conditions of sealed, undamaged packages are cool environmental temperature and dry storage facilities able to protect from weather and accidental damage.

HANDLING AND SAFETY

Detailed information about a safe treatment of the material are indicated in the "Material Safety Data Sheet" (MSDS) furnished with the first material supply. The MSDS may be also sent again in case of loss.

PREDRYING CONDITIONS (Hot-air dryer)

Predrying needed. Predrying conditions are: at least 2 hours at 250 ÷ 300°F. Increase time in case of damp material. Maximum suggested moisture content: 0.1%. Use of desiccant dryers or vacuum ovens allows a reduction in drying time. Vacuum ovens, desiccant dryers or forced ventilation ovens are suggested. Wet material appears darker.

BARREL TEMPERATURE PROFILE

Suggested barrel temperature profile (zone 1 - zone 2 - zone 3 - nozzle): 555-570-590-610°F.

RESIDENCE TIME

Maximum allowable residence time: 30 minutes. Do not exceed this limit. Maximum number of complete shots (in the barrel) suggested: 4 ÷ 8

MELT TEMPERATURE

Suggested range of melt temperature: 555 ÷ 625°F. On small machines, running short cycles, it is possible to use higher melt temperatures to improve plastification, fluidity and surface appearance, paying attention to any indication of material degradation. PAY ATTENTION! Do not exceed the suggested maximum temperature.

MOLD TEMPERATURE

Suggested range of mold temperature: 275 ÷ 300°F. This can be significantly different from the tool settings, due to the cooling system efficiency and the accuracy of the temperature control on the tool. If molding temperature is lower than suggested, part annealing may be necessary. High mould temperature is suggested. Low mold temperature is suggested.

INJECTION SPEED

Advisable injection speed: medium to high. Best results are achieved by using an injection profile. Low injection speed improve surface appearance.

TANGENTIAL SCREW VELOCITY (V)

Maximum suggested tangential velocity (V): 0.35 ÷ 0.65 fps. The maximum rotational speed may be calculated by means of the following equation: $\text{rpm} = S/d \cdot 229$, where d is the screw diameter (in).

INJECTION PRESSURE

Maximum advisable injection pressure at nozzle: 50 ÷ 130 MPa. Please, check on manual of injection molding machine the ratio between specific pressure (at nozzle) and hydraulic pressure (of oil).

PACKING PRESSURE

Typical suggested packing pressure (at nozzle): 70 ÷ 100% of injection pressure.

CUSHION

Minimum suggested cushion: 0.10 ÷ 0.25 in.

BACK PRESSURE

Suggested backpressure: 45 ÷ 100 psi (hydraulic pressure).

REGRIND USAGE

Maximum suggested regrind percentage: 15%. In-loop regrind is suggested. Regrind must be dried. Unless otherwise specified in yellow card, UL guidelines allow up to 25% regrind to be used without affecting the rating. Otherwise, it is recommended that Customer downloads the yellow card and attaches it to this documentation. In any case, LATI advises not to use more than 15%.

VALVE GATES / SMALL GATES

Use of valve gates or small injection gates is not recommended due to risk of clogging.

MATERIAL HANDLING

Pneumatic conveyor systems should be avoided to prevent the separation of the steel bundles from the base resin. Avoid use of pneumatic conveyor systems or forced air dryers to prevent separation between resin and additives.

EQUIPMENT WEAR AND CORROSION

Usually, critical processing conditions (high injection rate, high back pressure and high screw rotating speed, etc.) and/or disadvantageous geometric conditions (low wall thickness, low diameters, sharp fillet radius, etc.) generate wear on equipment. Wear increases in case of filled materials (particularly fibers filled ones). Appropriate surface treatments of equipment are suggested in these cases, as well as a proper venting to avoid material overheating. Steel types containing a high chrome percentage (Cr > 13%) or a specific surface treatment (e.g. Chrome or Nickel electroplating) are suggested. It is advisable to use a wear-resistant steel to make the mold.

APPROVALS

Please, check our site or contact LATI for details.

CONTACTS

LATI Industria Termoplastici S.p.A.