

LATILUB 80-05T G/30

Self-lubricating product based on Polyphenylene Sulphide (PPS). PTFE. Glass fibers. Intrinsically flame retardant.

The products mentioned herein are not suitable for applications in contact with foodstuffs or for potable water transportation, or for toy manufacturing.

The products mentioned herein are not suitable for applications in the pharmaceutical, medical or dental sector.

PHYSICAL PROPERTIES	STANDARD	VALUE MEASURE UNITS
Density	ISO 1183	1.61 g/cm ³
Linear shrinkage at moulding		
Longitudinal (0.078in/8,700psi)	ISO 294-4	0.15 ÷ 0.35 %
Transversal (0.078in/8,700psi)	ISO 294-4	0.50 ÷ 0.75 %
Dimensional stability	---	68
Moisture absorption		
saturation, in air	ISO 62-4	0.02 %
MECHANICAL PROPERTIES	STANDARD	VALUE MEASURE UNITS
CHARPY impact strength		
Unnotched, at 23°F	ISO 179-1eU	17.5 ft.lb/in ²
Notched, at +23°F	ISO 179-1eA	4.0 ft.lb/in ²
MECHANICAL PROPERTIES	STANDARD	VALUE MEASURE UNITS
Tensile elongation		
At break (0.196 in/min), 23°F	ISO 527	1.5 %
Tensile strength		
At break (0.196 in/min), 23°F	ISO 527	21000 psi
Elastic modulus		
Tensile (0.04 in/min), 23°F	ISO 527	1950 kpsi
THERMAL PROPERTIES	STANDARD	VALUE MEASURE UNITS
Coefficient of linear thermal expansion (CLTE)		
30°F to 100°F (longitudinal)	ISO 11359	20 × 10 ⁻⁶ K ⁻¹
30°F to 100°F (transversal)	ISO 11359	40 × 10 ⁻⁶ K ⁻¹
VICAT - Softening point		
11 lb (heating rate 250°F/h)	ISO 306	491 °F
HDT - Heat Deflection Temperature		
66 psi	ISO 75	527 °F
264 psi	ISO 75	518 °F
Thermal conductivity		
in plane	ASTM E 1461-92	2.1 W/(m·K)
through plane	ASTM E 1461-92	1.7 W/(m·K)
FLAMMABILITY	STANDARD	VALUE MEASURE UNITS
Flammability rating		
0.125 in. thickness	UL 94	V-0
0.060 in. thickness	UL 94	V-0
0.030 in. thickness	UL 94	V-0

LATILUB 80-05T G/30

FLAMMABILITY	STANDARD	VALUE	MEASURE	UNITS
GWFI - Glow Wire Flammability Index				
0.078 in. thickness	IEC 60695-2-12	960	°C	
0.040 in. thickness	IEC 60695-2-12	960	°C	
FLAMMABILITY	STANDARD	VALUE	MEASURE	UNITS
GWIT - Glow Wire Ignition Test				
0.078 in. thickness	IEC 60695-2-13	775	°C	
0.040 in. thickness	IEC 60695-2-13	775	°C	
ELECTRICAL PROPERTIES	STANDARD	VALUE	MEASURE	UNITS
CTI - Comparative Tracking Index				
solution A (without surfactant)	IEC 60112	125	V	
Electrical resistivity				
surface, dry	ASTM D 257 / ASTM D4496	1E12	ohm	
Dielectric strength (short period)				
0.078 in. thickness, 73°F, dry	ASTM D 149	457	kV/mm	
TRIBOLOGICAL PROPERTIES	STANDARD	VALUE	MEASURE	UNITS
Wear Factor				
	ASTM D 3702	85	10 ⁻⁸	(mm ³ /N m)
Friction Coefficient				
static	ASTM D 3702	0.29		
dynamic	ASTM D 3702	0.35		

STORAGE

Best storage conditions of sealed, undamaged packages are warm environmental temperature in dry storage facilities able to protect from weather and accidental damage.

HANDLING AND SAFETY

Detailed information about a safe treatment of the material are indicated in the "Material Safety Data Sheet" (MSDS) furnished with the first material supply. The MSDS may be also sent again in case of loss.

PREDRYING CONDITIONS (Hot-air dryer)

Predrying needed. Predrying conditions are: at least 2 hours at $250 \div 300^{\circ}\text{F}$. Increase time in case of damp material. Maximum suggested moisture content: 0.1%. Use of desiccant dryers or vacuum ovens allows a reduction in drying time.

BARREL TEMPERATURE PROFILE

Suggested barrel temperature profile (zone 1 - zone 2 - zone 3 - nozzle): $555\text{-}570\text{-}590\text{-}610^{\circ}\text{F}$.

RESIDENCE TIME

Maximum allowable residence time: 30 minutes. Do not exceed this limit. Maximum number of complete shots (in the barrel) suggested: $4 \div 8$

MELT TEMPERATURE

Suggested range of melt temperature: $555 \div 625^{\circ}\text{F}$. On small machines, running short cycles, it is possible to use higher melt temperatures to improve plastification, fluidity and surface appearance, paying attention to any indication of material degradation.

MOLD TEMPERATURE

Suggested range of mold temperature: $275 \div 300^{\circ}\text{F}$. This can be significantly different from the tool settings, due to the cooling system efficiency and the accuracy of the temperature control on the tool. If molding temperature is lower than suggested, part annealing may be necessary.

INJECTION SPEED

Advisable injection speed: medium to high. Best results are achieved by using an injection profile.

TANGENTIAL SCREW VELOCITY (V)

Maximum suggested tangential velocity (V): $0.35 \div 0.65$ fps. The maximum rotational speed may be calculated by means of the following equation: $\text{rpm} = S/d \cdot 229$, where d is the screw diameter (in).

INJECTION PRESSURE

Maximum advisable injection pressure at nozzle: $50 \div 130$ MPa. Please, check on manual of injection molding machine the ratio between specific pressure (at nozzle) and hydraulic pressure (of oil).

PACKING PRESSURE

Typical suggested packing pressure (at nozzle): $70 \div 100\%$ of injection pressure.

CUSHION

Minimum suggested cushion: $0.10 \div 0.25$ in.

BACK PRESSURE

Suggested backpressure: $45 \div 100$ psi (hydraulic pressure).

REGRIND USAGE

Maximum suggested regrind percentage: 15%. In-loop regrind is suggested. Regrind must be dried.

HOT RUNNER MOLDS

Hot runner molds can be used when a very tight temperature control is assured.

VALVE GATES / SMALL GATES

Valve gates or small injection gates can be used.

EQUIPMENT WEAR AND CORROSION

Usually, critical processing conditions (high injection rate, high back pressure and high screw rotating speed, etc.) and/or disadvantageous geometric conditions (low wall thickness, low diameters, sharp fillet radius, etc.) generate wear on equipment. Wear increases in case of filled materials (particularly fibers filled ones). Appropriate surface treatments of equipment are suggested in these cases, as well as a proper venting to avoid material overheating. Steel types containing a high chrome percentage (Cr > 13%) or a specific surface treatment (e.g. Chrome or Nickel electroplating) are suggested. It is advisable to use a wear- and corrosion-resistant steel to make the mold.

Check the proper "Molding guide" for further details.

APPROVALS

Please, check our site or contact LATI for details.

CONTACTS

LATI Industria Termoplastici S.p.A.