

LATIOHM 85-06 PD01 G/15

Semiconductive/dissipative product based on Polyethersulphone (PESU). Glass fibres. Intrinsically flame retardant. PFAS-free product.

The products mentioned herein are not suitable for applications in contact with foodstuffs or for potable water transportation, or for toy manufacturing.

The products mentioned herein are not suitable for applications in the pharmaceutical, medical or dental sector.

PHYSICAL PROPERTIES	STANDARD	VALUE MEASURE UNITS
Density	ISO 1183	1.50 g/cm ³
Linear shrinkage at moulding		
Longitudinal (2.0mm/60MPa)	ISO 294-4	0.10 ÷ 0.25 %
Transversal (2.0mm/60MPa)	ISO 294-4	0.25 ÷ 0.45 %
Dimensional stability	---	73
Moisture absorption		
saturation, in air	ISO 62-4	0.60 %
at saturation, in water	ISO 62-4	1.60 %
Melt Flow Index (MFI) - 380°C/2.16kg	ASTM D 1238	16.00 g/10'
MECHANICAL PROPERTIES	STANDARD	VALUE MEASURE UNITS
CHARPY impact strength		
Unnotched, at 23°C	ISO 179-1eU	25.0 kJ/m ²
Unnotched, at -20°C	ISO 179-1eU	25.0 kJ/m ²
Notched, at 23°C	ISO 179-1eA	6.0 kJ/m ²
Notched, at -20°C	ISO 179-1eA	6.0 kJ/m ²
MECHANICAL PROPERTIES	STANDARD	VALUE MEASURE UNITS
Tensile elongation		
At break (5 mm/min), 23°C	ISO 527	1.4 %
At break (5 mm/min), 60°C	ISO 527	1.2 %
At break (5 mm/min), 90°C	ISO 527	1.2 %
At break (5 mm/min), 120°C	ISO 527	1.2 %
At break (5 mm/min), 150°C	ISO 527	1.0 %
Tensile strength		
At break (5 mm/min), 23°C	ISO 527	145 MPa
At break (5 mm/min), 60°C	ISO 527	135 MPa
At break (5 mm/min), 90°C	ISO 527	125 MPa
At break (5 mm/min), 120°C	ISO 527	105 MPa
At break (5 mm/min), 150°C	ISO 527	95 MPa
Elastic modulus		
Tensile (1 mm/min), 23°C	ISO 527	13500 MPa
Tensile (1 mm/min), 60°C	ISO 527	13500 MPa
Tensile (1 mm/min), 90°C	ISO 527	13000 MPa
Tensile (1 mm/min), 120°C	ISO 527	12000 MPa
Tensile (1 mm/min), 150°C	ISO 527	10500 MPa

LATIOHM 85-06 PD01 G/15

THERMAL PROPERTIES

Coefficient of linear thermal expansion (CLTE)

30°C to 100°C (longitudinal)

STANDARD

ISO 11359

VALUE MEASURE UNITS

25 × 10⁻⁶ K⁻¹

30°C to 100°C (transversal)

ISO 11359

55 × 10⁻⁶ K⁻¹

VICAT - Softening point

50 N (heating rate 120°C/h)

ISO 306

215 °C

HDT - Heat Deflection Temperature

0.45 MPa

ISO 75

220 °C

1.81 MPa

ISO 75

210 °C

Thermal conductivity

in plane

ASTM E 1461-92

0.3 W/(m·K)

through plane

ASTM E 1461-92

0.3 W/(m·K)

FLAMMABILITY

STANDARD

VALUE MEASURE UNITS

GWFI - Glow Wire Flammability Index

2 mm thickness

IEC 60695-2-12

960 °C

3 mm thickness

IEC 60695-2-12

960 °C

GWIT - Glow Wire Ignition Test

2 mm thickness

IEC 60695-2-13

825 °C

3 mm thickness

IEC 60695-2-13

875 °C

ELECTRICAL PROPERTIES

STANDARD

VALUE MEASURE UNITS

Electrical resistivity

surface, dry

ASTM D 257 / ASTM D4496

2E2 ohm

volume

ASTM D 257 / ASTM D4496

2E2 ohm.cm

STORAGE

Best storage conditions of sealed, undamaged packages are warm environmental temperature in dry storage facilities able to protect from weather and accidental damage.

HANDLING AND SAFETY

Detailed information about a safe treatment of the material are indicated in the "Material Safety Data Sheet" (MSDS) furnished with the first material supply. The MSDS may be also sent again in case of loss.

PREDRYING CONDITIONS (Hot-air dryer)

Predrying needed. Predrying conditions are: at least 3 hours at 130 ÷ 170°C. Increase time in case of wet material. Maximum suggested moisture content: 0.05%. Use of desiccant dryers or vacuum ovens allows a reduction in drying time.

BARREL TEMPERATURE PROFILE

Suggested barrel temperature profile (zone 1 - zone 2 - zone 3 - nozzle): 325-350-365-365°C.

RESIDENCE TIME

Maximum allowable residence time: 10 minutes. Do not exceed this limit. Maximum number of complete shots (in the barrel) suggested: 2 ÷ 3

MELT TEMPERATURE

Suggested range of melt temperature: 350 ÷ 380°C. On small machines, running short cycles, it is possible to use higher melt temperatures to improve plastification, fluidity and surface appearance, paying attention to any indication of material degradation.

MOULD TEMPERATURE

Suggested range of mould temperature: 150 ÷ 190°C. This can be significantly different from the tool settings, due to the cooling system efficiency and the accuracy of the temperature control on the tool. If moulding temperature is lower than suggested, part annealing may be necessary.

INJECTION SPEED

Advisable injection speed: medium. Best results are achieved by using an injection profile.

TANGENTIAL SCREW VELOCITY (V)

Maximum suggested tangential velocity (V): 0.1 ÷ 0.2 m/s. The maximum rotational speed (in rpm) may be calculated by means of the following equation: $rpm = V/d * 19100$, where d is the screw diameter (mm).

INJECTION PRESSURE

Maximum advisable injection pressure at nozzle: 80 ÷ 150 MPa. Please, check on manual of injection moulding machine the ratio between specific pressure (at nozzle) and hydraulic pressure (of oil).

PACKING PRESSURE

Typical suggested packing pressure (at nozzle): 50 ÷ 90% of injection pressure.

CUSHION

Minimum suggested cushion: 3 ÷ 6 mm.

BACK PRESSURE

Suggested backpressure: 3 ÷ 5 bar (hydraulic pressure).

REGRIND USAGE

Maximum suggested regrind percentage: 15%. In-loop regrind is suggested. Regrind must be dried.

HOT RUNNER MOULDS

Hot runner moulds can be used when a very tight temperature control is assured.

VALVE GATES / SMALL GATES

Use of valve gates or small injection gates has to be evaluated due to risk of clogging.

EQUIPMENT WEAR AND CORROSION

Usually, critical processing conditions (high injection rate, high back pressure and high screw rotating speed, etc.) and/or disadvantageous geometric conditions (low wall thickness, low diameters, sharp fillet radius, etc.) generate wear on equipment. Wear increases in case of filled materials (particularly fibres filled ones). Appropriate surface treatments of equipment are suggested in these cases, as well as a proper venting to avoid material overheating. Steel types containing a high chrome percentage (Cr > 13%) or a specific surface treatment (e.g. Chrome or Nickel electroplating) are suggested. It is advisable to use a high wear-resistant steel to make the mould.

Check the proper "Moulding guide" for further details.

APPROVALS

Please, check our site or contact LATI for details.

CONTACTS

LATI Industria Termoplastici S.p.A.