

LATAMID 66 H2 G/50

Compound based on Polyamide 66 (PA 66). Improved thermal stabilization. Glass fibers. PFAS-free product.

Versions of product mentioned herein are suitable for applications in contact with foodstuffs or for toy manufacturing. Nevertheless, manufactured parts have to be verified according to the specific directives.

The products mentioned herein are not suitable for applications in the pharmaceutical, medical or dental sector.

PHYSICAL PROPERTIES

	STANDARD	VALUE MEASURE UNITS
Density	ISO 1183	1.57 g/cm ³
Linear shrinkage at moulding		
Longitudinal (0.078in/8,700psi)	ISO 294-4	0.30 ÷ 0.60 %
Transversal (0.078in/8,700psi)	ISO 294-4	0.60 ÷ 0.90 %
Dimensional stability	---	65
Moisture absorption		
saturation, in air	ISO 62-4	1.25 %

MECHANICAL PROPERTIES

CHARPY impact strength

Unnotched, at 23°F	ISO 179-1eU	42.5 ft.lb/in ²
Unnotched, at -20°F	ISO 179-1eU	40.0 ft.lb/in ²
Notched, at +23°F	ISO 179-1eA	7.0 ft.lb/in ²
Notched, at +/-20°F	ISO 179-1eA	6.0 ft.lb/in ²

MECHANICAL PROPERTIES

Tensile elongation

At break (0.196 in/min), 23°F	ISO 527	2.4 %
At break (0.196 in/min), 60°F	ISO 527	3.4 %
At break (0.196 in/min), 90°F	ISO 527	3.8 %
At break (0.196 in/min), 120°F	ISO 527	3.9 %
At break (0.196 in/min), 150°F	ISO 527	4.0 %

Tensile strength

At break (0.196 in/min), 23°F	ISO 527	34500 psi
At break (0.196 in/min), 60°F	ISO 527	26250 psi
At break (0.196 in/min), 90°F	ISO 527	21000 psi
At break (0.196 in/min), 120°F	ISO 527	17250 psi
At break (0.196 in/min), 150°F	ISO 527	15000 psi

Elastic modulus

Tensile (0.04 in/min), 23°F	ISO 527	2250 kpsi
Tensile (0.04 in/min), 60°F	ISO 527	1650 kpsi
Tensile (0.04 in/min), 90°F	ISO 527	1380 kpsi
Tensile (0.04 in/min), 120°F	ISO 527	1020 kpsi
Tensile (0.04 in/min), 150°F	ISO 527	960 kpsi

LATAMID 66 H2 G/50

THERMAL PROPERTIES	STANDARD	VALUE	MEASURE UNITS
Coefficient of linear thermal expansion (CLTE)			
30°F to 100°F (longitudinal)	ISO 11359	20	$\times 10^{-6} \text{ K}^{-1}$
30°F to 100°F (transversal)	ISO 11359	45	$\times 10^{-6} \text{ K}^{-1}$
VICAT - Softening point			
11 lb (heating rate 250°F/h)	ISO 306	491	°F
HDT - Heat Deflection Temperature			
66 psi	ISO 75	500	°F
264 psi	ISO 75	491	°F
FLAMMABILITY	STANDARD	VALUE	MEASURE UNITS
Oxygen Index			
	ASTM D 2863	27	%
Flammability rating			
0.125 in. thickness	UL 94	HB	
0.060 in. thickness	UL 94	HB	
0.030 in. thickness	UL 94	HB	
ELECTRICAL PROPERTIES	STANDARD	VALUE	MEASURE UNITS
Electrical resistivity			
surface, dry	ASTM D 257 / D 4496	1E12	ohm
Dielectric strength (short period)			
0.078 in. thickness, 73°F, dry	ASTM D 149	559	kV/mm

STORAGE

Best storage conditions of sealed, undamaged packages are warm environmental temperature in dry storage facilities able to protect from weather and accidental damage. PAY ATTENTION! Material is prone to absorb moisture.

HANDLING AND SAFETY

Detailed information about a safe treatment of the material are indicated in the "Material Safety Data Sheet" (MSDS) furnished with the first material supply. The MSDS may be also sent again in case of loss.

PREDRYING CONDITIONS (Hot-air dryer)

Predrying needed. Predrying conditions are: at least 2 hours at $175 \div 210^{\circ}\text{F}$. Increase time in case of damp material. Maximum suggested moisture content: 0.1%. Use of desiccant dryers or vacuum ovens allows a reduction in drying time.

BARREL TEMPERATURE PROFILE

Suggested barrel temperature profile (zone 1 - zone 2 - zone 3 - nozzle): 520-535-555-565°F.

RESIDENCE TIME

Maximum allowable residence time: $10 \div 12$ minutes. Do not exceed this limit. Maximum number of complete shots (in the barrel) suggested: $2 \div 6$

MELT TEMPERATURE

Suggested range of melt temperature: $535 \div 570^{\circ}\text{F}$. On small machines, running short cycles, it is possible to use higher melt temperatures to improve plastification, fluidity and surface appearance, paying attention to any indication of material degradation.

MOLD TEMPERATURE

Suggested range of mold temperature: $175 \div 210^{\circ}\text{F}$. This can be significantly different from the tool settings, due to the cooling system efficiency and the accuracy of the temperature control on the tool. If molding temperature is lower than suggested, part annealing may be necessary.

INJECTION SPEED

Advisable injection speed: medium to high. Best results are achieved by using an injection profile.

TANGENTIAL SCREW VELOCITY (V)

Maximum suggested tangential velocity (V): $0.65 \div 1.00$ fps. The maximum rotational speed may be calculated by means of the following equation: $\text{rpm} = S/d \cdot 229$, where d is the screw diameter (in).

INJECTION PRESSURE

Maximum advisable injection pressure at nozzle: $70 \div 140$ MPa. Please, check on manual of injection molding machine the ratio between specific pressure (at nozzle) and hydraulic pressure (of oil).

PACKING PRESSURE

Typical suggested packing pressure (at nozzle): $50 \div 60\%$ of injection pressure.

CUSHION

Minimum suggested cushion: $0.10 \div 0.30$ in.

BACK PRESSURE

Suggested backpressure: $45 \div 220$ psi (hydraulic pressure).

REGRIND USAGE

Maximum suggested regrind percentage: 15%. In-loop regrind is suggested. Regrind must be dried.

HOT RUNNER MOLDS

Hot runner molds can be used when a very tight temperature control is assured.

VALVE GATES / SMALL GATES

Use of valve gates or small injection gates has to be evaluated due to risk of clogging.

EQUIPMENT WEAR AND CORROSION

Usually, critical processing conditions (high injection rate, high back pressure and high screw rotating speed, etc.) and/or disadvantageous geometric conditions (low wall thickness, low diameters, sharp fillet radius, etc.) generate wear on equipment. Wear increases in case of filled materials (particularly fibers filled ones). Appropriate surface treatments of equipment are suggested in these cases, as well as a proper venting to avoid material overheating. It is advisable to use a wear-resistant steel to make the mold.

Check the proper "Molding guide" for further details.

APPROVALS

Please, check our site or contact LATI for details.

CONTACTS

LATI Industria Termoplastici S.p.A.