

LATAMID 66 H2 K/30

Compound based on Polyamide 66 (PA 66). Improved thermal stabilisation. Carbon fibres. PFAS-free product.

The products mentioned herein are not suitable for applications in contact with foodstuffs or for potable water transportation, or for toy manufacturing.

The products mentioned herein are not suitable for applications in the pharmaceutical, medical or dental sector.

PHYSICAL PROPERTIES

	STANDARD	VALUE MEASURE UNITS
Density	ISO 1183	1.27 g/cm ³
Linear shrinkage at moulding		
Longitudinal (2.0mm/60MPa)	ISO 294-4	0.15 ÷ 0.35 %
Transversal (2.0mm/60MPa)	ISO 294-4	0.55 ÷ 0.85 %
Dimensional stability	---	59
Moisture absorption		
saturation, in air	ISO 62-4	1.75 %

MECHANICAL PROPERTIES

CHARPY impact strength

Unnotched, at 23°C	ISO 179-1eU	55.0 kJ/m ²
Unnotched, at -20°C	ISO 179-1eU	50.0 kJ/m ²
Notched, at 23°C	ISO 179-1eA	8.0 kJ/m ²
Notched, at -20°C	ISO 179-1eA	7.0 kJ/m ²

MECHANICAL PROPERTIES

Tensile elongation

At break (5 mm/min), 23°C	ISO 527	1.9 %
At break (5 mm/min), 60°C	ISO 527	2.7 %
At break (5 mm/min), 90°C	ISO 527	3.4 %
At break (5 mm/min), 120°C	ISO 527	3.5 %
At break (5 mm/min), 150°C	ISO 527	3.6 %

Tensile strength

At break (5 mm/min), 23°C	ISO 527	250 MPa
At break (5 mm/min), 60°C	ISO 527	195 MPa
At break (5 mm/min), 90°C	ISO 527	145 MPa
At break (5 mm/min), 120°C	ISO 527	115 MPa
At break (5 mm/min), 150°C	ISO 527	90 MPa

Elastic modulus

Tensile (1 mm/min), 23°C	ISO 527	21600 MPa
Tensile (1 mm/min), 60°C	ISO 527	17600 MPa
Tensile (1 mm/min), 90°C	ISO 527	11000 MPa
Tensile (1 mm/min), 120°C	ISO 527	7400 MPa
Tensile (1 mm/min), 150°C	ISO 527	6400 MPa

LATAMID 66 H2 K/30

THERMAL PROPERTIES	STANDARD	VALUE	MEASURE	UNITS
Coefficient of linear thermal expansion (CLTE)				
30°C to 100°C (longitudinal)	ISO 11359	10	$\times 10^{-6}$	K ⁻¹
30°C to 100°C (transversal)	ISO 11359	40	$\times 10^{-6}$	K ⁻¹
VICAT - Softening point				
50 N (heating rate 120°C/h)	ISO 306	255		°C
HDT - Heat Deflection Temperature				
0.45 MPa	ISO 75	260		°C
1.81 MPa	ISO 75	250		°C
ELECTRICAL PROPERTIES	STANDARD	VALUE	MEASURE	UNITS
Electrical resistivity				
surface, dry	ASTM D 257 / ASTM D4496	1E3		ohm
volume	ASTM D 257 / ASTM D4496	5E3		ohm.cm
Dielectric strength (short period)				
2 mm thickness, 23°C, dry	ASTM D 149	3		kV/mm

STORAGE

Best storage conditions of sealed, undamaged packages are warm environmental temperature in dry storage facilities able to protect from weather and accidental damage. PAY ATTENTION! Material is prone to absorb moisture.

HANDLING AND SAFETY

Detailed information about a safe treatment of the material are indicated in the "Material Safety Data Sheet" (MSDS) furnished with the first material supply. The MSDS may be also sent again in case of loss.

PREDRYING CONDITIONS (Hot-air dryer)

Predrying needed. Predrying conditions are: at least 2 hours at $80 \div 100^{\circ}\text{C}$. Increase time in case of wet material. Maximum suggested moisture content: 0.1%. Use of desiccant dryers or vacuum ovens allows a reduction in drying time.

BARREL TEMPERATURE PROFILE

Suggested barrel temperature profile (zone 1 - zone 2 - zone 3 - nozzle): 270-280-285-290°C.

RESIDENCE TIME

Maximum allowable residence time: $10 \div 12$ minutes. Do not exceed this limit. Maximum number of complete shots (in the barrel) suggested: $2 \div 6$

MELT TEMPERATURE

Suggested range of melt temperature: $280 \div 300^{\circ}\text{C}$. On small machines, running short cycles, it is possible to use higher melt temperatures to improve plastification, fluidity and surface appearance, paying attention to any indication of material degradation.

MOULD TEMPERATURE

Suggested range of mould temperature: $80 \div 100^{\circ}\text{C}$. This can be significantly different from the tool settings, due to the cooling system efficiency and the accuracy of the temperature control on the tool. If moulding temperature is lower than suggested, part annealing may be necessary.

INJECTION SPEED

Advisable injection speed: medium to high. Best results are achieved by using an injection profile.

TANGENTIAL SCREW VELOCITY (V)

Maximum suggested tangential velocity (V): $0.2 \div 0.3$ m/s. The maximum rotational speed (in rpm) may be calculated by means of the following equation: $\text{rpm} = V/d * 19100$, where d is the screw diameter (mm).

INJECTION PRESSURE

Maximum advisable injection pressure at nozzle: $70 \div 140$ MPa. Please, check on manual of injection moulding machine the ratio between specific pressure (at nozzle) and hydraulic pressure (of oil).

PACKING PRESSURE

Typical suggested packing pressure (at nozzle): $50 \div 60\%$ of injection pressure.

CUSHION

Minimum suggested cushion: $3 \div 8$ mm.

BACK PRESSURE

Suggested backpressure: $3 \div 15$ bar (hydraulic pressure).

REGRIND USAGE

Maximum suggested regrind percentage: 15%. In-loop regrind is suggested. Regrind must be dried.

HOT RUNNER MOULDS

Hot runner moulds can be used when a very tight temperature control is assured.

VALVE GATES / SMALL GATES

Valve gates or small injection gates can be used.

EQUIPMENT WEAR AND CORROSION

Usually, critical processing conditions (high injection rate, high back pressure and high screw rotating speed, etc.) and/or disadvantageous geometric conditions (low wall thickness, low diameters, sharp fillet radius, etc.) generate wear on equipment. Wear increases in case of filled materials (particularly fibres filled ones). Appropriate surface treatments of equipment are suggested in these cases, as well as a proper venting to avoid material overheating. It is advisable to use a wear-resistant steel to make the mould.

Check the proper "Moulding guide" for further details.

APPROVALS

Please, check our site or contact LATI for details.

CONTACTS

LATI Industria Termoplastici S.p.A.