

## LATAMID 6 BH

Compound based on Polyamide 6 (PA 6). Low viscosity. Heat stabilized. PFAS-free product.

Versions of product mentioned herein are suitable for applications in contact with foodstuffs within the conditions permitted by the material, or for toy manufacturing. Nevertheless, manufactured parts have to be verified according to the specific directives.

The products mentioned herein are not suitable for applications in the pharmaceutical, medical or dental sector.

PHYSICAL PROPERTIES	STANDARD	VALUE MEASURE UNITS
<b>Density</b>	ISO 1183	<b>1.13</b> g/cm <sup>3</sup>
<b>Linear shrinkage at moulding</b>		
Longitudinal (2.0mm/60MPa)	ISO 294-4	<b>1.05 ÷ 1.35</b> %
Transversal (2.0mm/60MPa)	ISO 294-4	<b>1.15 ÷ 1.40</b> %
<b>Dimensional stability</b>	---	<b>72</b>
<b>Moisture absorption</b>		
saturation, in air	ISO 62-4	<b>2.50</b> %
MECHANICAL PROPERTIES	STANDARD	VALUE MEASURE UNITS
<b>CHARPY impact strength</b>		
Unnotched, at 23°C	ISO 179-1eU	<b>NB</b> kJ/m <sup>2</sup>
Unnotched, at -20°C	ISO 179-1eU	<b>NB</b> kJ/m <sup>2</sup>
Notched, at 23°C	ISO 179-1eA	<b>3.5</b> kJ/m <sup>2</sup>
Notched, at -20°C	ISO 179-1eA	<b>3.0</b> kJ/m <sup>2</sup>
MECHANICAL PROPERTIES	STANDARD	VALUE MEASURE UNITS
<b>Tensile elongation</b>		
At yield (5 mm/min), 23°C	ISO 527	<b>3.5</b> %
At yield (5 mm/min), 60°C	ISO 527	<b>&gt;10</b> %
At yield (5 mm/min), 90°C	ISO 527	<b>&gt;10</b> %
At yield (5 mm/min), 120°C	ISO 527	<b>&gt;10</b> %
At yield (5 mm/min), 150°C	ISO 527	<b>&gt;10</b> %
At break (5 mm/min), 23°C	ISO 527	<b>30.0</b> %
At break (5 mm/min), 60°C	ISO 527	<b>&gt;50</b> %
At break (5 mm/min), 90°C	ISO 527	<b>&gt;50</b> %
At break (5 mm/min), 120°C	ISO 527	<b>&gt;50</b> %
At break (5 mm/min), 150°C	ISO 527	<b>&gt;50</b> %
<b>Tensile strength</b>		
At yield (5 mm/min), 23°C	ISO 527	<b>80</b> MPa
At yield (5 mm/min), 60°C	ISO 527	<b>25</b> MPa
At yield (5 mm/min), 90°C	ISO 527	<b>20</b> MPa
At yield (5 mm/min), 120°C	ISO 527	<b>15</b> MPa
At yield (5 mm/min), 150°C	ISO 527	<b>10</b> MPa
At break (5 mm/min), 23°C	ISO 527	<b>80</b> MPa
At break (5 mm/min), 60°C	ISO 527	<b>NB</b> MPa
At break (5 mm/min), 90°C	ISO 527	<b>NB</b> MPa
At break (5 mm/min), 120°C	ISO 527	<b>NB</b> MPa
At break (5 mm/min), 150°C	ISO 527	<b>NB</b> MPa

# LATAMID 6 BH

MECHANICAL PROPERTIES	STANDARD	VALUE MEASURE UNITS
<b>Elastic modulus</b>		
Tensile (1 mm/min), 23°C	ISO 527	3000 MPa
Tensile (1 mm/min), 60°C	ISO 527	650 MPa
Tensile (1 mm/min), 90°C	ISO 527	400 MPa
Tensile (1 mm/min), 120°C	ISO 527	350 MPa
Tensile (1 mm/min), 150°C	ISO 527	300 MPa
<b>THERMAL PROPERTIES</b>		
<b>Coefficient of linear thermal expansion (CLTE)</b>		
30°C to 100°C (longitudinal)	ISO 11359	90 × 10 <sup>-6</sup> K <sup>-1</sup>
30°C to 100°C (transversal)	ISO 11359	90 × 10 <sup>-6</sup> K <sup>-1</sup>
<b>VICAT - Softening point</b>		
50 N (heating rate 120°C/h)	ISO 306	200 °C
<b>HDT - Heat Deflection Temperature</b>		
0.45 MPa	ISO 75	165 °C
1.81 MPa	ISO 75	60 °C
<b>Thermal conductivity</b>		
in plane	ASTM E 1461-92	0.3 W/(m·K)
through plane	ASTM E 1461-92	0.3 W/(m·K)
<b>FLAMMABILITY</b>		
<b>Oxygen Index</b>		
	ASTM D 2863	23 %
<b>Flammability rating</b>		
3 mm thickness	UL 94	V-2
0.75 mm thickness	UL 94	V-2
<b>ELECTRICAL PROPERTIES</b>		
<b>Electrical resistivity</b>		
surface, dry	ASTM D 257 / D 4496	1E12 ohm
<b>Dielectric strength (short period)</b>		
2 mm thickness, 23°C, dry	ASTM D 149	18 kV/mm

#### STORAGE

Best storage conditions of sealed, undamaged packages are warm environmental temperature in dry storage facilities able to protect from weather and accidental damage. PAY ATTENTION! Material is prone to absorb moisture.

#### HANDLING AND SAFETY

Detailed information about a safe treatment of the material are indicated in the "Material Safety Data Sheet" (MSDS) furnished with the first material supply. The MSDS may be also sent again in case of loss.

#### PREDRYING CONDITIONS (Hot-air dryer)

Predrying needed. Predrying conditions are: at least 2 hours at 70 ÷ 90°C. Increase time in case of wet material. Maximum suggested moisture content: 0.15%. Use of desiccant dryers or vacuum ovens allows a reduction in drying time. Vacuum ovens, desiccant dryers or forced ventilation ovens are suggested. Wet material appears darker.

#### BARREL TEMPERATURE PROFILE

Suggested barrel temperature profile (zone 1 - zone 2 - zone 3 - nozzle): 235-240-245-245°C.

#### RESIDENCE TIME

Maximum allowable residence time: 8 ÷ 10 minutes. Do not exceed this limit. Maximum number of complete shots (in the barrel) suggested: 2 ÷ 8

#### MELT TEMPERATURE

Suggested range of melt temperature: 230 ÷ 250°C. On small machines, running short cycles, it is possible to use higher melt temperatures to improve plastification, fluidity and surface appearance, paying attention to any indication of material degradation. PAY ATTENTION! Do not exceed the suggested maximum temperature.

#### MOULD TEMPERATURE

Suggested range of mould temperature: 60 ÷ 90°C. This can be significantly different from the tool settings, due to the cooling system efficiency and the accuracy of the temperature control on the tool. If moulding temperature is lower than suggested, part annealing may be necessary. High mould temperature is suggested. Low mould temperature is suggested.

#### INJECTION SPEED

Advisable injection speed: medium to high. Best results are achieved by using an injection profile. Low injection speed improve surface appearance.

#### TANGENTIAL SCREW VELOCITY (V)

Maximum suggested tangential velocity (V): 0.3 ÷ 0.4 m/s. The maximum rotational speed (in rpm) may be calculated by means of the following equation:  $\text{rpm} = V/d * 19100$ , where d is the screw diameter (mm).

#### INJECTION PRESSURE

Maximum advisable injection pressure at nozzle: 70 ÷ 140 MPa. Please, check on manual of injection moulding machine the ratio between specific pressure (at nozzle) and hydraulic pressure (of oil).

#### PACKING PRESSURE

Typical suggested packing pressure (at nozzle): 50 ÷ 60% of injection pressure.

#### CUSHION

Minimum suggested cushion: 3 ÷ 8 mm.

#### BACK PRESSURE

Suggested backpressure: 3 ÷ 15 bar (hydraulic pressure).

#### REGRIND USAGE

Maximum suggested regrind percentage: 15%. In-loop regrind is suggested. Regrind must be dried. Unless otherwise specified in yellow card, UL guidelines allow up to 25% regrind to be used without affecting the rating. Otherwise, it is recommended that Customer downloads the yellow card and attaches it to this documentation. In any case, LATI advises not to use more than 15%.

#### VALVE GATES / SMALL GATES

Valve gates or small injection gates can be used.

#### **MATERIAL HANDLING**

Pneumatic conveyor systems should be avoided to prevent the separation of the steel bundles from the base resin. Avoid use of pneumatic conveyor systems or forced air dryers to prevent separation between resin and additives.

#### **EQUIPMENT WEAR AND CORROSION**

Usually, critical processing conditions (high injection rate, high back pressure and high screw rotating speed, etc.) and/or disadvantageous geometric conditions (low wall thickness, low diameters, sharp fillet radius, etc.) generate wear on equipment. Wear increases in case of filled materials (particularly fibres filled ones). Appropriate surface treatments of equipment are suggested in these cases, as well as a proper venting to avoid material overheating. Steel types containing a high chrome percentage (Cr > 13%) or a specific surface treatment (e.g. Chrome or Nickel electroplating) are suggested. Standard steel can be used to make the mould.

#### **APPROVALS**

**Please, check our site or contact LATI for details.**

#### **CONTACTS**

**LATI Industria Termoplastici S.p.A.**