HK:+852-69575415 China GuangDong:+13538586433 ShangHai:+18816996168

GLOBALPRENE 5517D Styrene-Isoprene block copolymer 苯乙烯-異戊二烯 嵌段共聚合物

Features 特性：

- Linear block copolymer 線狀嵌段共聚物
- Low strength and low viscosity 低強度及低黏度
- Triblock and diblock copolymer 三嵌段及雙嵌段共聚物

Typical Application 一般應用：

- Hot melt adhesive 熱熔膠
- Solvent base adhesive 溶劑膠

Typical Properties：	Test Method	Unit	Value	Range
一般性質	測試方法	單位	數值	範圍
SM Content 苯乙烯含量	ASTM D5775	%	15	13 ~ 17
Diblock 雙嵌段	ASTM D5296	%	38	35 ~ 40
Specific Gravity 比重	ASTM D792	g/cc	0.93	N/A
Volatile Matter 揮發份	ASTM D5668	%	0.25	≤ 0.8
Ash Content 灰份	ASTM D5667	%	0.3	≤ 0.5
Melt Flow Index (190℃, 5kg) 熔融流動指數	ASTM D1238	g/10min	20	15 ~ 25
25wt% / 25℃ Toluene Viscosity 25wt% / 25℃甲苯黏度	ASTM D2196	cP	800	650 ~ 950

Packing 包裝： 25 kg paper bag 25 公斤 纸袋
600 kg super bag 600 公斤 太空包

All ingredients in the products are in compliance with the following chemical inventories：

United States: Toxics Substances Control Act Inventory (TSCA)

Canada: Domestic Substances List (DSL)

Europe: EINECS/ELINCS replaced by REACH

Australia: Australian Inventory of Chemical Substances (AICS)

New Zealand: New Zealand Inventory of Chemicals (NZIoC)

Korea: Korean Existing Chemicals List (KECL)

Japan: Japanese Inventory of Existing and New Chemical Substances (ENCS)

The Philippines: Philippines Inventory of Chemicals and Chemical Substances (PICCS)

China: Inventory of Existing Chemical Substances Manufactured or Imported in China (IECSC)

Taiwan: Existing Chemical Substances Inventory (ECSI)