



Globalprene 9924 Maleated Styrene-Ethylene/Butylene block copolymer 馬來酸酐苯乙烯-乙烯/丁烯嵌段共聚物

Features 特性 : <ul style="list-style-type: none"> • Linear triblock copolymer 線狀嵌段共聚物 • Excellent heat resistance 優良的耐熱性 • High adhesive application 高黏著應用 • Improve impact of plastics 提升塑膠耐衝擊性 		Typical Application 一般應用 : <ul style="list-style-type: none"> • Plastic modification 塑料改質 • Adhesives 黏著增黏劑 • Overmolding modification 包膠增黏劑 • Asphalt modification 瀝青改質 			
Typical Properties : 一般性質		Test Method 測試方法	Unit 單位	Value 數值	Range 範圍
SM Content 苯乙烯含量		ASTM D5775	%	13	11.5 ~ 14.5
Specific Gravity 比重		ASTM D792	g/cc	0.90	≥ 0.90
Maleic anhydride ratio 馬來酸酐接枝率		LCY	%	1.5	0.8 ~ 3.0
Volatile Matter 揮發份		ASTM D5668	%	0.3	≤ 0.5
Ash Content 灰份		ASTM D5667	%	0.5	≤ 1.0
MFI (230°C / 5kg)		ASTM D1238	g/min	20	15 ~ 40

Note : SM content is measured on polymer before hydrogenation. 苯乙烯含量為氫化前測量值

Packing 包裝 : 20kg paper bag 20 公斤紙袋

All ingredients in the products are in compliance with the following chemical inventories :

United States: Toxics Substances Control Act Inventory (TSCA)

Canada: Non-Domestic Substances List (NDSL)

Europe: EINECS/ELINCS replaced by REACH

Australia: Australian Inventory of Chemical Substances (AICS)

New Zealand: New Zealand Inventory of Chemicals (NZIoC)

Korea: Korean Existing Chemicals List (KECL)

Japan: Japanese Inventory of Existing and New Chemical Substances (ENCS)

The Philippines: Philippines Inventory of Chemicals and Chemical Substances (PICCS)

China: Inventory of Existing Chemical Substances Manufactured or Imported in China (IECSC)

Taiwan: Existing Chemical Substances Inventory (ECSI)