



Technical Data Sheet

| GLOBALPRENE 3741 Styrene-Butadiene block copolymer | | | | |
|--|---------|--|-----------|-------------|
| Features: | | Typical Application: | | |
| Radial block copolymer | | Asphalt modification, compounding Solvent-based adhesives | | |
| Typical Properties | Unit | Typical Value | Range | Test Method |
| Specific Gravity | g/cc | 0.94 | N/A | ASTM D 792 |
| Volatile Matter | % | 0.21 | 1.0 max | ASTM D 5668 |
| Ash Content | % | 0.1 | 1.0 max | ASTM D 5667 |
| Bound Styrene | % | 30 | 29 - 33 | - |
| Molecular Weight x1000 | Daltons | 250 | 230 – 260 | ASTM D 5296 |
| Coupling Efficiency | % | 90 | 85 min. | ASTM D 5296 |

Packaging: 450 kg super sack

All ingredients in the products are in compliance with the following chemical inventories :

United States: Toxics Substances Control Act Inventory (TSCA)

Canada: Domestic Substances List (DSL)

Europe: EINECS/ELINCS replaced by REACH

Australia: Australian Inventory of Chemical Substances (AICS)

New Zealand: New Zealand Inventory of Chemicals (NZIoC)

Korea: Korean Existing Chemicals List (KECL)

Japan: Japanese Inventory of Existing and New Chemical Substances (ENCS)

The Philippines: Philippines Inventory of Chemicals and Chemical Substances (PICCS)

China: Inventory of Existing Chemical Substances Manufactured or Imported in China (IECSC)

Taiwan: Existing Chemical Substances Inventory (ECSI)